UDK 616.31(091)
COBISS.SR-ID 38719497

ИСТОРИЈА ИМПЛАНТОЛОГИЈЕ СА АСПЕКТА ОСЕОИНТЕГРАЦИЈЕ И МУКОИНТЕГРАЦИЈЕ

Милован Стевић (1), Зоран Татић(1), Владимир Биочанин (2), Душан Ђурић (3), Игор Ђукић (4)

(1) КЛИНИКА ЗА СТОМАТОЛОГИЈУ, ОДЕЉЕЊЕ ЗА ИМПЛАНТОЛОГИЈУ, ВОЈНО-МЕДИЦИНСКА АКАДЕМИЈА, БЕОГРАД; (2) КЛИНИКА ЗА ОРАЛНУ ХИРУРГИЈУ И ДЕНТАЛНУ ИМПЛАНТОЛОГИЈУ, СТОМАТОЛОШКИ ФАКУЛТЕТ У ПАНЧЕВУ, УНИВЕРЗИТЕТ ПРИВРЕДНА АКАДЕМИЈА У НОВОМ САДУ; (3) КАТЕДРА ЗА КЛИНИЧКУ ФАРМАЦИЈУ, ФАКУЛТЕТ МЕДИЦИНСКИХ НАУКА, УНИВЕРЗИТЕТ У КРАГУЈЕВЦУ; (4) ДЕНТАЛНА КЛИНИКА, МЕДИЦИНСКИ ФАКУЛТЕТ, БАЊА ЛУКА

Сажетак: Тежња да се надоместе изгубљени зуби имплантацијом страног материјала стара је колико и сама цивилизација. Убрзани развој имплантологије као науке креће тек од средине прошлог века. Централно место у имплантологији заузима процес осеоинтеграције. Највеће заслуге за овај феномен припадају проф. Пер Ингвар Бренемарку који је случајним открићем увидео могућност потпуне инкорпорације титанијумског имплантата у околну кост. Открићем осеоинтеграције и дефинисањем услова који је омогућавају започиње период развоја имплантологије са унапређењем ендоосеалне имплантације у ефикасну методу протетске рехабилитације, предвидивог исхода и продуженог века трајања имплантата и зубне надокнаде у функцији. Импантологија је у почетку имала за циљ да унапреди функцију и квалитет живота безубих и крзубих пацијената, а од 90-их година постаје протетски вођена не само функционалним него и естетским принципима. Са почетком 21. века, имплантологија је усмерена на унапређење изгледа и стабилности меких ткива чиме започиње ера мукоинтеграције.

Кључне речи: историја имплантологије, осеоинтеграција, мукоинтеграција

УВОД

Иако имплантологија као наука последњих деценија доживљава процват, треба се сетити да историја имплантологије сеже у давна времена. На основу археолошких истраживања налазимо да су Кинези још пре 4000 година користили шиљке бамбусових стабала и уграђивали у виличну кост као замену за изгубљене зубе. Стари Египћани, Етрурци, а касније и Феничани су користили племените метале, обрађене воловске кости или кости слоноваче и уграђивали их у коштано ткиво. Ови иновативни народи користили су златне жице за стабилизацију расклаћених зуба [1,2].

Хипократ (5. век пре нове ере) писао је о могућности учвршћивања вештачких зуба користећи златни или свилени конач како би реплантирао извађене зубе, саветујући практиканта да „не одбацује извађене зубе или зубе избачене из повређене мандибуле, већ да их враћа на место, везујући их за преостале зубе златним нитима“ [3.] Исту препоруку дао је и Аулу

Корнелиус Целсус (1. век пре нове ере) који је у часопису „Де Медицина“ споменуо могућност замене недостајућег зуба имплантацијом зуба, узетом са кадавера, код оних који су из различитих разлога изгубили зуб; међутим, није известио да ли је такав третман успешан. Ипак, мора се напоменути да је главна сврха ових замена била козметичка, док се мастикаторна функција није пуно разматрала [3].

Познато је да су још припадници племена Маје у 7. веку користили разне материјале у естетске сврхе, као што су тиркиз, кварц, серпентине итд. и утискивали у пажљиво припремљене просторе на вестибуларним површинама углавном предњих зуба. Посебно је занимљив налаз Вилсона Попеноеа и његове супруге Дороти током истраживања цивилизације Маја у Хондурасу где су пронашли фрагмент мандибуле у коме су у алвеолама некада присутних секутића налазе три реплике зуба израђених од шкољке. У проучавању овог необичног налаза, чланови експедиције су испрва претпоставили да су уметнути

HISTORY OF IMPLANTOLOGY FROM THE ASPECT OF OSSEOINTEGRATION AND MUCOINTEGRATION

Milovan Stević (1), Zoran Tatić(1), Vladimir Biočanin (2), Dušan Đurić (3), Igor Đukić (4)

(1) DENTAL CLINIC, DEPARTMENT FOR IMPLANTOLOGY, MILITARY MEDICAL ACADEMY, BELGRADE; (2) CLINIC FOR ORAL SURGERY AND DENTAL IMPLANTOLOGY, SCHOOL FOR DENTISTRY IN PANCEVO „UNIVERSITY BUSINESS ACADEMY IN NOVI SAD”; (3) DEPARTMENT FOR CLINIC PHARMACY, FACULTY OF MEDICAL SCIENCES, UNIVERSITY OF KRAGUJEVAC; (4) DENTAL CLINIC, FACULTY OF MEDICINE, BANJA LUKA

Summary: The tendency to replace lost teeth by implanting foreign material is as old as civilization itself. The accelerated development of implantology as a science started only in the middle of the last century. The essence of implantology is the process of osseointegration. The greatest merits for this phenomenon belong to prof. Per Ingvar Brenemark, who accidentally discovered the possibility of complete incorporation of a titanium implant into the surrounding bone. With the discovery of osseointegration and defining the conditions that enable it, the period of implantology development begins with the improvement of endosseous implantation into an efficient method of prosthetic rehabilitation, predictable outcome and extended lifespan of implants and dental restoration in function. Implantology initially aimed to improve the function and quality of life of partial and complete edentulous patients, and since the 1990s it has become prosthetically guided not only by functional but also by aesthetic principles. With the beginning of the 21st century, implantology is aimed at improving the appearance and stability of soft tissues, thus beginning the era of mucointegration.

Key words: history of implantology, osseointegration, mucointegration

INTRODUCTION

Although implantology as a science has flourished in recent decades, it should be remembered that the history of implantology stretches back to ancient times. Based on archaeological research, we find that 4,000 years ago, the Chinese used spikes of bamboo trees and implanted them in the jaw bone as a substitute for lost teeth. The ancient Egyptians, the Etruscans, and later the Phoenicians used noble metals, processed ox bones or ivory and implanted them in bone tissue. These innovative nations used gold wires to stabilize disassembled teeth [1,2].

Hippocrates (5th century BC) wrote about the possibility of hardening artificial teeth using gold or silk thread to replicate the teeth removed, advising the practitioner not to "discard the teeth or teeth removed from the injured mandibula, but to return them to place, tying them to the remaining teeth with golden threads" [3]. The same recommendation was made by Aulus Cornelius Celsus (1st century BC) which in the journal "De Medicina" mentioned

the possibility of replacing the missing tooth with a dental implant, taken from the cadaver, in those who lost a tooth for different reasons; however, he did not report whether such treatment was successful. However, it must be noted that the main purpose of these replacements was cosmetic, while the function of mastication was not much considered [3].

It is known that Mayans in the 7th century used various materials for aesthetic purposes, such as turquoise, quartz, serpentine, etc. and inserted carefully prepared spaces on the vestibular surfaces of mostly front teeth. Particularly interesting is the findings of Wilson Popenoe and his wife Dorothy during a survey of the Mayan civilization in Honduras, where they found a fragment of mandibula containing three replica teeth made of shellfish in alveolas. In studying this unusual find, expedition members initially assumed that the inserted elements were cosmetic treatments post-mortem, possibly as part of a complicated funeral ritual or religious practice [4].

елементи козметички третмани post-mortem, вероватно као део компликованог погребног

ритуала или религиозне праксе [4].

Слика 1. Налаз доње вилице припадника цивилизације Маја из 7. века пронађен у Хондурасу. (Преузето са: <http://www.implantmn.com/about-dental-implants/history-and-types-of-dental-implants/> у научне сврхе а не користи се у комерцијалне сврхе)

Радиографски снимци мандибуле 1970. године показују формирање кости око имплантата која невероватно личи на оно што се види око савремених имплантата. Ово је изгледа био први аутентични алопластични материјал уграђен за живота у хумано ткиво. Недавна и исцрпна хистолошка истраживања о понашању фрагмената школке у директном контакту са коштаном ткивом у експериментима са животињама потврдила је принцип осеинтеграције између два ткива [3,6,7].

Све до средине 19. века забележени су бројни покушаји реплантације и трансплантације зуба где су се истицали радови Пареа, Дупонта, Фушарда и других, али се није много одмакло у развоју имплантологије. У 19-ом и почетком 20-ог века оснивачи Балтиморске школе, даље Магиоло, Бонвил, Грам, Паине и други користили су различите материјале, платину, олово, сребро, злато, иридијум, керамику, а користили су имплантате облика цилиндра, шупљег шрафа, пуног шрафа, цилиндричне мрежице, спирале, игле и др.

Иако се ови случајеви не могу сматрати у потпуности успешним, мора се нагласити да су током овог века, од Магиола до Паинеа истраживачи прогресивно покушавали, барем на концептуалном нивоу, да користе све више "инертне" материјале, и то је паралелно са развојем концепта уградње алопластичних имплантата с ретензивном морфологијом [6,7].

Године 1938. Шведњанин Густав Дахл, поставио је субпериостални мандибуларни

имплантат са четири метална стуба изнад десни на које је касније усидрена протеза. Важно је напоменути да је након овог покушаја Шведско стоматолошко друштво од њега затражило да се одмах уздржи од спровођења третмана, а казна је избацивање из друштва управо у тренутку када се чинило да је процедура била предодређена за успех [8,9].

У Бостону 1939. године, браћа Струок, започела су испитивања имплантата од Виталијума, легуре хром, молибдена и кобалта коју су већ тестирали на псима. Дизајн субпериостеалних имплантата су даље истражили и разрадили Лев, Бауш и Берман 1950. [8,9.] На конференцији одржаној у Милану 27. фебруара 1947. године, Италијан Манлио Формиђини предложио је шупљи спирални вијак од нерђајуће челичне жице или тантала, Дизајнер је методу назвао „директном ендоалвеоларном имплантацијом“ и означио дефинитивни прелаз у еру ендосеалних имплантата. Формиђини је тада представио неколико клиничких случајева и са собом довео два пацијента који су жвакали без проблема са фиксним протезама [9]. Стоматолошки свет је доживео оправдан период опрезног скептицизма према ендосеалним имплантатима и нада се, уместо тога, полагала у могући успех најновије технике субпериостеалних имплантата. Као резултат тога, неуспеси (услед техничких грешака првих ученика Формиђинија) били су узети у обзир више од успеха када су у питању званичне пресуде [3,8,9].

Picture 1. The find of a 7th-century mandible of the Mayan civilization was found in Honduras. (Taken from <http://www.implantmn.com/about-dental-implants/history-and-types-of-dental-implants/> for scientific purposes and not used for commercial purposes)

Radiographs of mandible in 1970. showed the formation of a bone around the implants that resembles what is seen around modern implants. This appears to have been the first authentic aloplastic material implanted in human tissue during life. Recent and exhaustive histological research on the behaviour of shell fragments in direct contact with bone tissue in experiments with animals has confirmed the principle of oseointegration between the two tissues [3,6,7].

Until the mid-19th century numerous attempts at replantation and dental transplantation were recorded, where the works of Pare, Dupont, Fauchard and others were not much advanced in the development of implantology. In the 19th and early 20th centuries, the founders of the Baltimore School, further Maggiolo, Bonville, Gram, Paine and others used various materials, platinum, lead, silver, gold, iridium, ceramics, and used cylinder-shaped implants, hollow screws, full screws, cylindrical nets, spirals, needles, etc.

Although these cases cannot be considered entirely successful, it must be noted that during this century, from Maggiolo to Paine, researchers have progressively tried, at least on a conceptual level, to use more and more inert materials, and this is in accordance with the development of the concept of implanting aloplastic implants with retentional morphology [6,7].

In 1938, Sweden's Gustav Dahl installed a subperiosteal mandibular implant with four metal columns above the gums that were later anchored to the braces. It is important to note that after this attempt, the Swedish Dental Society asked him to immediately refrain from conducting the treatment, and the punishment was expelled from society at the very moment

when the procedure appeared destined for success [8,9].

In Boston in 1939. the Strock brothers began testing of vitalium implants, chromium alloys, molibden and cobalt that they had already tested on dogs. The design of subperiosteal implants was further explored and developed by Lew, Baush and Berman in 1950. [8,9]. At a conference in Milan on 27 february 1947. Italy's Manlio Formiggini proposed a hollow spiral bolt made of stainless steel wire or tantal. The Designer called the method "direct endoalveolar implantation" and marked a definitive transition to an era of endoseal implants. Formigjni then presented several clinical cases and brought with him two patients who chewed without problems with fixed dentures [9]. The dental world has experienced a justifiable period of cautious skepticism towards endoseal implants and hopes instead to make the latest subperiosteal implant technique possible. As a result, failures (due to technical errors by formigni's first students) were taken into account more than success when it came to official verdicts [3,8,9].

OSSEOINTEGRATION

Osseointegration as a concept is introduced by Per-Ingvar Branemark (1969), professor at the Institute of Applied Biotechnology, University of Gothenburg. He defined it as "a direct structural and functional connection between the living bone and the surface of the implant". He came to this phenomenon by accident. He observed microcirculation of the bone and the healing of the wounds through the titanium tube that he incorporated into the rabbit fibula. When he tried to remove the chamber after the experiment, he noticed that it had grown with bone tissue and could not be easily removed.

ОСЕОИНТЕГРАЦИЈА

Осеоинтеграцију као концепт уводи Пер-Ингвар Бранемарк (1969), професор на Институту за примењену биотехнологију, Универзитета у Гетеборгу. Дефинисао ју је "директном структуралном и функционалном везом између живе кости и површине имплантата". Он је до овог феномена дошао случајним открићем. Посматрао је микроциркулацију кости и заостаје рана кроз титанијумску цев коју је инкорпорирао у зечију фибулу. Када је по завршетку експеримента покушао да уклони комору приметио је да је срасла са коштаном ткивом и да се не може лако уклонити. Тада је открио раст костију на површини коморе од титанијума и добру интеграцију имплантата са кости. Феномен је назвао осеоинтеграција [11,12,13,14]. Осеоинтеграција је изведена од грчке речи за кост „остеон“, и латинске „интеграре“, што значи направити целину [11]. Претпостављало се да коштаном сидрење по принципу осеоинтеграције може да делује и код људи, а први пацијенти без зуба лечени су 1965. године [11,12,13,14].

У то време осеоинтеграција није била прихваћен феномен. Иако су и експерименти на животињама изведени у Бренемарковој лабораторији јасно показали да је могуће усидрење у кости под условом да се поштују основне смернице, научна заједница није била уверена у осеоинтеграцију јер је изостао хистолошки доказ. Тек средином 1970. године А. Шредер је користећи новоразвијену технику резања недекалцифициране кости и имплантата без раздвајања усидрених делова показао да је реч о осеоинтеграцији. То је био први доказ директног споја имплантата и кости. Оригинални Бранемарков имплантат је створен као цилиндричан; касније су се појавили конични облици [13,14,15]. Дизајни имплантата доживели су пробој 1960-их, а основни дизајн спирале модификовао је др Леонард Линков 1963. године у имплантат облика оштрице са могућношћу да се постави у максилу и мандибулу што је данас познато као ендосеална имплантација [8,14].

Године 1978. одржана је Харвард Консензусна конференција ради успостављања консензуса о употреби имплантата на Харвард универзитету, а стандард за успешан имплантат је био да ли

је имплантат остао уграђен и функционалан пет година. Овај стандард се може чинити изузетно кратким, али илуструје каква су тада била очекивања од третмана имплантата [8,16]. Током осамдесетих година прошлог века професор Зарб са Универзитета у Торонту имао је централну улогу у одржавању Торонто конференције о осеоинтеграцији у клиничкој стоматологији, на којој је Бранемарк представио резултате својих истраживања током 30 и клиничку праксу скоро 20 година. Са овом конференцијом као прекретницом, Бранемарков режим се проширио Северном Америком. Типични Бранемарк-ов режим током овог периода састојао се од уградње четири до шест имплантата у доњој вилици и препоручивао хируршку двостепену технику која је постала широко распрострањена у целом свету [8,16].

Средином 80-их, уобичајени имплантат који су користили многи стоматолози био је имплантат коренског облика. Главни фактори који су одређивали који је систем имплантата одабран у односу на други, укључују дизајн, храпавост површине, протетска разматрања, једноставност уметања у кост, трошкове и успешност у одређеном временском периоду [17].

Након бројних клиничких студија, заслугама др Бренемарка, Шредера, Штраумана, а посебно др Зарба осамдесетих година прошлог века шири се индикацијско подручје за уградњу денталних имплантата са искључиво безубих и на крезубе вилице пацијената. Резултати успешне осеоинтеграције пењу се на више од 90 % па имплантологија доживљава и комерцијални процват и бива прихваћена као валидна терапијска дисциплина [15,18,19].

Ово доба карактерише појава нових и модификација старих дизајна као и појава нових хируршких техника. Основу ове нове филозофије чинила је осеоинтеграција и низ предуслова које треба испунити да би она била остварена. Албрекссон (Albrektsson) и сар. (1981) објавили су препоруке о низу фактора које би требало предузети за успешну осеоинтеграцију. Осеоинтеграција представља директну везу кости и имплантата, без уметнутих слојева. Ипак, не долази до 100 %-тног развоја везе кости и имплантата. Зато и дефиниција

That's when he discovered bone growth on the surface of the titanium chamber and good integration of bone implants. The phenomenon was called oseointegration [11,12,13,14]. Oseointegration is derived from the Greek word for bone "osteon", and Latin "integrare", which means to create a whole [11]. It was assumed that bone anchoring on the principle of feeling could work in humans, and the first toothless patients were treated in 1965. [11,12,13,14].

At the time, the osseointegration was not an accepted phenomenon. Although experiments on animals conducted in Branemark's laboratory made it clear that it was possible to anchor the bone on the condition that basic guidelines were observed, the scientific community was not convinced of the osseointegration because histological evidence was absent. It wasn't until mid-1970, A. Schroeder, using a newly developed technique of cutting non-decalized bones and implants without separating anchored parts, showed that it was osseointegration. It was the first evidence of a direct connection of implants and bone. The original Branemark implant was created as a cylindrical; later, the conical shapes appeared [13,14,15]. Implant designs were breakthrough in the 1960s, and the basic spiral design was modified by Dr Leonard Linkow in 1963. the implant of the shape of the blade with the ability to place in maxillo and mandibul, which is now known as endosseal implantation [8,14].

In 1978, The Harvard Consensus Conference was held to establish a consensus on the use of implants at Harvard University, and the standard for a successful implant was whether the implant remained implanted and functional for five years. This standard may seem extremely short, but it illustrates what the expectations of implant treatment were at the time [8,16].

During the 1980s, Professor Zarb of the University of Toronto played a central role in holding the Toronto Conference on Oseointegration in Clinical Dentistry, where Branemark presented the results of his research over 30 years and clinical practice for nearly 20 years. With this conference as a turning point, the Branemark regime has expanded across North America. The typical Branemark regime during this period consisted of implanting four to six implants in the lower jaw and recommended a surgical two-stage technique that became widespread worldwide [8,16].

In the mid-1980s, a common implant used by many dentists was a root-shaped implant. The main factors that determined which implant system was selected relative to the other, included design, surface roughness, prosthetic considerations, simplicity of insertion into the bone, costs and success over a certain period of time [17].

After numerous clinical studies, the merits of Dr. Brennanmark, Schroeder, Strauman, and especially Dr. Zarb in the 1980s expanded the indication area for the implantation of dental implants from the purely toothless and toothless jaws of patients. The results of successful oseointegration climb to more than 90 per cent, so implantology is also experiencing a commercial boom and is accepted as a valid therapeutic discipline [15,18,19].

This age is characterized by the emergence of new and modification of old designs as well as the emergence of new surgical techniques. The basis of this new philosophy consisted of oseointegration and a number of preconditions that need to be met in order for it to be achieved. Albrektsson et al. (1981) published educations about a number of factors to be taken for successful oseointegration. Oseointegration is a direct link between bone and implants, without inserted layers. However, it does not occur to 100 per cent - the development of bone and implant connections. Therefore, the definition of oseointegration is based on stability, not histological criteria, which reads "the process of achieving clinically asymptomatic rigid fixation of alloplastic material in the bone, during the functional load" [13,17]. Some scientists believe that only a biomechanical factor determines whether a fibrous capsule or bone will be created around the implant [13,18]. Contrary to this understanding, there is well-documented evidence of how the bone's response is quantitatively different depending on the type of biomaterials and the roughness of its surface. [13,20]. The surface of the dental implant is the only part that is in contact with the biological environment, and the uniqueness of the surface directs the response and affects the mechanical strength of the contact of the implants / tissue [20,21]. One of the main reasons for modifying the surfaces of dental implants is the reduction of oseointegration time. This may include mechanical treatments (for example processing and sanding), chemical treatments (acid-

осеоинтеграције се темељи на стабилности, а не на хистолошким критеријумима, а која гласи „процес постизања клинички асимптоматске ригидне фиксације алопластичног материјала у кости, током функционалног оптерећења“ [13,17]. Неки научници верују да само биомеханички фактор одређује хоће ли се око имплантата створити фиброзна капсула или кост [13,18]. Насупрот овом схватању постоји добро документован доказ о томе како је одговор кости квантитативно другачији зависно о типу биоматеријала и храпавости његове површине [13,20]. Површина зубног имплантата је једини део који је у контакту са биолошким окружењем, а јединственост површине усмерава одговор и утиче на механичку чврстоћу контакта имплантата/ткива [20,21]. Један од главних разлога модификације површина зубних имплантата је смањење времена осеоинтеграције. Ово може да укључује механичке третмане површине имплантата (на пример обрада и пескирање), хемијске третмане (нагризање киселином), електрохемијске третмане (анодна оксидација), вакумске третмане, термичке и ласерске третмане. Површински слој на имплантату је потребан за повећање функционалне површине додиром кости-имплантата тако да се стрес ефикасно преноси. Поред тога, површински премаз поспешује апозицију кости. Најновије иновације зубних имплантата укључују употребу флуора, хидрокси-апатита, антибиотика, фактора раста и ламинана [20,21].

Деведесетих година концепт протетика вођена хирургијом бива замењен концептом хирургија вођена протетиком те се фокус интересовања оралне имплантологије премешта са функционалног и на естетски аспект. Мање или више, имедијатно оптерећење бива замењено одложеним. Такође, уводе се и процедуре коштаних аугментација са циљем надокнаде изгубљене кости и постављања имплантата у правилну позицију. Такозвани ткивни инжињеринг, отвара потпуно нове видике у

планирању, али и у извођењу имплантолошких захвата [22].

Рачунарски дизајнирани начин производње као и компјутеризовани тродимензионални модели користе се за предвиђање карактеристика расподеле стреса у имплантатима око кости. У недавним клиничким студијама Блашке (Blaschke) и сарадници су известили да су зубни имплантати направљени од цирконије адекватна алтернатива титанијским зубним имплантатима. Поред одличних естетских резултата, аутори закључују да цирконијумски имплантати омогућавају степен осеоинтеграције и реакције меког ткива који је бољи од титанијумских зубних имплантата [23,24].

МУКОИНТЕГРАЦИЈА

Као што је познато, унапређење зубних имплантата су вршена да се омогући оптималан ниво осеоинтеграције. Међутим постоји и други фактор који је јако важан, здравље меког ткива. Добро је познато да за здравље зуба периодонтално ткиво није битно само што стабилизује зубе, већ представља баријеру између усне шупљине и зуба. Улога меког ткива је прилично слична и када су у питању имплантати: контакт густог меког ткива и површине абатмента може деловати као баријера да заштити и чува фундаменталну кресталну кост. Анатомске карактеристике меког ткива и суседног имплантата се разликују од меког ткива око природне дентиције. Перпедикуларна колагена влакна позната као Шарпејева влакна везују природне зубе за цемент, док колагена влакна теже да адхерирају за површину абатмента у паралелним или циркумференцијалном снопу, што је слабији спој. Зато је и научна заједница последњих година усмерена на побољшање здравља периимплантног меког ткива, здравља папиле око имплантата, мењају се имплантатне платформе, површине абатмента у циљу бољег функционалног прилагођавања меког ткива. Мукогингивалном хирургијом (Pedicule grafts, гингивални графт, слободни везивно-ткивни графт итд.) може се унапредити изглед периимплантатне контуре [25,26,27].

etching), electrochemical treatments (anodine oxidation), vacuum treatments, thermal and laser treatments. The surface layer on the implant is needed to increase the functional surface of the bone-implant touch so that stress is transmitted effectively. In addition, surface coating accelerates bone apposition. The latest innovations in dental implants include the use of fluoride, hydroxy-apatite, antibiotics, growth factors and lamina [20,21].

In the 1990s, the concept of prosthetics guided by surgery was replaced by the concept of prosthetic guided surgery and the focus of interest in oral implantology shifted from functional and aesthetic aspects. More or less, the immediate loading is replaced by delayed. Also, procedures of bone augmentation are being introduced to compensate for lost bone and put the implants in the correct position. So-called tissue engineering opens up completely new horizons in planning, but also in the performance of implant procedures [22].

Computer-designed production methods as well as computerized three-dimensional models are used to predict stress distribution characteristics in the implants around the bone. In recent clinical studies Blaschke and al. reported that dental implants made of zirconium are an adequate alternative to titanium dental implants. In addition to excellent aesthetic results, the authors conclude that zirconium implants enable a degree of osseointegration and soft tissue reaction that is better than titanium dental implants [23,24].

MUCOINTEGRATION

As it is known, the improvement of dental implants was done to enable optimal levels of osseointegration. However, there is another factor that is very important, the health of soft tissue. It is well known that for the health of the teeth, periodontal tissue is not only important because it stabilizes the teeth, it is a barrier between the oral cavity and the teeth. The role of soft tissue is quite similar when it comes to implants: contact between dense soft tissue and the surface of the abutment can act as a barrier to protecting and preserving the fundamental crestal bone. The anatomical characteristics of soft tissue and adjacent implants differ from soft tissue around natural dentation. Perpendicular collagen fibres known as Sharpey fibers bind natural teeth to cement, while collagen fibers tend to adhere for the surface of the abutment in parallel or circular beads, which is a weaker combination. That's why the scientific community in recent years has been focused on improving the health of periimplant soft tissue, the health of the papilla around the implants, changing implant platforms, surfaces of abutments in order to better functionally adapt soft tissue. Mucogingival surgery (Pedicule grafts, gingival graft, free connective-tissue graft, etc.) can improve the appearance of periimplant contours [25,26,27].

Слика 2. Поређење карактеристика пародонта и периимплантног меког ткива. Шарпејева колагена влакна се везују за цемент корена зуба у перпендикуларном снопу, док су периимплантна влакна оријентисана циркумференцијално или паралелно са површином абатмента. (Преузето са: www.nobelbiocare.com/blog/science/why-abutment-surface-matters-for-soft-tissue-health/ / научне сврхе а не користи се у комерцијалне сврхе)

За дуготрајан успех, неопходно је постићи стабилност меког ткива око имплантата. Увођење „протетски вођеног мекоткивног растања“ у имплантолошку терапију има за циљ кондиционирање ткива пре дефинитивне протетске надокнаде, формирање оптималног излазног профила круне због постизања боље гингивалне естетике и превенције компликација. Код овог концепта привремене круне или индивидуализовани абатменти пружају потпору периимплантантним ткивима и папилама, постојећим или реконструисаним у фази имплантације, осигуравајући позитивну гингивалну архитектуру без губитка волумена и вестибуларне рецесије услед колапса меких ткива [22].

Површина имплантата је битан фактор за дуготрајно преживљавање, али је улога површине абатмента најмање испитивана па је последњих година предмет данашњих истраживача. Као што је показано у бројним студијама, абатменти са глатком површином не олакшавају механичко чишћење, али слабо акумулирају плак у односу на оне са грубљом површином. Два су фактора значајна за везу меког ткива: нанотопографија и површинска хемија. [24,28,29,30,31,32]. Нанотопографија површине абатмента постаје све важнија у објашњењу везе меког ткива. Верује се да површинска наноструктура игра важну улогу у интеракцији између ћелије и импланта на ћелијском и протеинском нивоу [33]. Постоје бројне методе за мењање

нанотопографије површине абатмента. Једна од њих преферира метод анодизације, метод који укључује потапање абатмента у електролитичку течност уз примену волтаже. Ове промене нанотопографије које доводе до везивања и пролиферације фибробласта је важан корак ка везивању меког ткива [34,35]. Процес анодизације је такође важан и за површинску хемију и енергију. Истраживања показују да анодизоване површине имају доста хидроксилних група које снажно корелирају и повећавају хидрофилност или афинитет површине за воду, односно крв [34,36]. Такође је показано да хидрофилна површина абатмента а priori може помоћи у адхезији, у подршци везе везе меког ткива, који је функционални и биолошки лепак и баријера и превенција микробиолошке колонизације [34,35,36,37,38].

Постоји јасна потреба да површина абатмента остане чиста и нетакнута пре коришћења, како би се постигао заштитни слој кроз употребу. Атмосферски елементи се могу надоградити на површину абатмента иако је у стерилном паковању. Ови депозити теже да имају негативне ефекте на енергију површине који су корелисани са хидрофилношћу и са заступљености хидрофилних група [39,40].

Када је једна од водећих светских имплантолошких кућа Nobel Biocare презентovala најновију површину абатмента Heal (заштићено име) и заједно са TiUltra (заштићено име) имплантатном

Figure 2. A comparison of the characteristics of periodontal and periimplant soft tissue. Sharpey collagen fibers are attached to the cement of the root of the teeth in the perpendicular bead, while the periimplant fibers are oriented circumferentially or parallel to the surface of the abutment. (Taken from www.nobelbiocare.com/blog/science/why-abutment-surface-matters-for-soft-tissue-health/ for scientific purposes and not used for commercial purposes)

For long-term success, it is necessary to achieve soft tissue stability around implants. The introduction of "prosthetic-guided soft healing" in implant therapy aims to condition tissue before definitive prosthetic compensation, form an optimal emergence profile of the crown for achieving a gingive aesthetic and complication prevention. In this concept, temporary crowns or individualized abutments provide support to periimplant tissues and papillas, existing or reconstructed during the implantation phase, ensuring positive gingive architecture without loss of volume and vestibular recession due to the collapse of soft tissues [22].

The surface of the implant is an important factor for long-term survival, but the role of the abutment surface has been least examined and has been the subject of today's researchers in recent years. As has been shown in numerous studies, smooth surface abutments do not facilitate mechanical cleaning, but they accumulate little plaque compared to those with rougher surfaces. Two factors are important for soft tissue connection: nanotopography and surface chemistry [24,28,29,30,31,32]. Nanotopography of the abutment surface becomes increasingly important in explaining the connection between soft tissue. Surface's nanostructure is believed to play an important role in the interaction between cells and implants at the cellular and protein levels. [33] There are numerous methods for changing the

nanotopography of the abutment surface. One of them prefers the method of anodization, a process that involves immersing the abutment into electrolytic fluid using voltage. These changes in nanotopography that lead to binding and proliferation of fibroblasts is an important step towards binding soft tissue [34,35]. The anode process is also important for surface chemistry and energy. Research shows that anodized surfaces have a lot of hydroxyl groups that correlates strongly and increases hydrophilicity or affinity surface for water, or blood [34,36]. It has also been shown that hydrophilic surface of abutment and priorities can help with adhesion, in support of soft tissue connection, which is functional and biological seal and barrier and prevention of microbial colonization [34,35,36,37,38].

There is a clear need for the abutment surface to remain clean and intact before use, in order to achieve a protective layer through use. Atmospheric elements can be upgraded to the surface of the abutment even though it is in sterile packaging. These deposits tend to have adverse effects on surface energy that are correlated with hydrophilicity and the representation of hydroxyl groups [39,40].

When one of the world's leading implant companies, Nobel Biocare, presented the newest surface of the Xeal abutment and together with Ti-ultra implant surface marked the beginning of an era of mucointegration. A

површином означили су почетак ере мукоинтеграције. Глатка, непорозна, наноструктурна, анодизована површина поседује површинску хемију и топографију која је дизајнирана да постигне мекоћивну везу. Кроз Heal и TiUltra Nobel biocare примењује процес анодизације на цео имплантни систем, од абатмента преко самог импланта до врха. Исте године су промовисали „on 1“ концепт који подразумева међуструктуру, on 1 base, који се поставља на имплантат у фази хируршке уградње и остаје на тој позицији и за време протетске рестаурације чиме се минимализује траума меког ткива. Платформа се тиме преноси са нивоа кости на ниво меког ткива. Иако је ова површина абатмента представљена на тржишту 2019. године, она је већ предмет клиничке студије са праћењем од две године у којој је показано статистички значајно повећање висине кератинизованог меког ткива у поређењу с машинским абатментима [29,41,42]. Поред функционалног бенефита, њена златна нијанса (резултат процеса анодизације) је корисна у подржавању природног изгледау трансмукозној зони, што може бити посебно релевантно у случајевима када је присутна танка слузокожа или рецесија слuzнице. Да би се обезбедио услов нетакнутости, носачи круне се испоручују са заштитним слојем који се раствара након контакта са течномшћу, тј. крвљу. Ова технологија сувог паковања чува површине абатмента хидрофилним и хемију површине и штити је од контаминације угљоводоникима [43].

РАЗВОЈ ИМПЛАНТОЛОШКЕ МИСЛИ У СРБИЈИ

Са открићем осеоинтеграције почиње и убрзани развој имплантологије у свету па и код нас. То је период када настају и први покушаји уградње имплантата у Србији. Давне 1963. Године, др Тавчар, др Шкоклев и др Спаић на ВМА чине прве покушаје имплантације два субпериостална импланта у безубој доњој вилицы, али су након три године експлантирани. Након неуспеха имплантације завладао је скептицизам све до 1977. Године када су др Шкундрић, др Спаић и др Шкоклев у пацијента са атрофичном и безубом горњом вилицом уградили „раније припремљене клинове од специјалне легуре“, који су у виду трипода учвршћени у кост алвеоларног наставка у пределу очњака и

првог молара обострано. На врховима клинова су постављене привремене круне од палапонта испуњене силикатом. Охрабрени успехом имплантацијске процедуре, у ВМА почињу да се примењују разни имплантати страних аутора, а посебно листасты, игличасты, вијак-имплантаты. Заслугама професора Перовића и Косовчевића пре свих, имплантологија почиње да се изучава и на студијама Стоматолошког факултета у Београду. Убрзо затим, 1981. Године у ВМА је уграђен први једноделни циркуларни листасты имплантат у доњој безубој вилицы [44]. Попут Бренемарка, Шредера, Штраумана и Зарба, др Шкундрић у Србији паралелно развија Б.Ц.Т. имплантни систем домаће производње настао као производ вишегодишње примене различитих система и стеченог искуства. Овај иновативни научник је у оквиру Б.Ц.Т. система инкорпорирао и део, мезоструктуру која неодољиво подсећа на оно што ће 30 година касније једна од водећих имплантолошких кућа Nobel biocare промовисати кроз свој концепт, on-1 којим је означила почетак ере мукоинтеграције.

ЗАКЉУЧАК

Осеоинтеграција је један од најкритичнијих аспеката успеха имплантата. Историја развоја и унапређења зубних имплантата је величанствено и фасцинантно путовање кроз време. На овом пољу истраживања и учења могуће је само зауставити и дивити се човековој инвентивности током година. Материјали од којих су зубни имплантаты израђивани крећу се од златне лигатурне жице, шкољки, слоноваче до хрома, кобалта, до иридијума и платине. Од спиралних дизајна имплантата од нерђајућег челика до двоструких спиралних креација и ендосеалних облика корена, стоматолошки истраживачи и клиничари су радили брзо и жестоко, створили су много структура како би заменили положаје које су некада имали природни зуби. Зубне површине су такође модификоване да би се смањило време за осеоинтеграцију. Модификоване површине укључују употребу хидроксиапатита, композита, угљеника, стакла, керамике као и титанијум оксида. Да би се спољашност учинила што је могуће погоднијом, површине имплантата су додатно пескиране,

smooth, non-porous, nanostructural, anodized surface has surface chemistry and topography that is designed to achieve soft tissue connection. Through Xeal and T-ultra Nobel biocare, it applies the anodization process to the entire implant system, from the abutment to the implant apex. That same year, they promoted the "on 1" concept, which involves an interstructure, on-1 base, which is placed on an implant in the surgical implant phase and remains in that position during prosthetic restoration, which minimizes soft tissue trauma. The platform is therefore transferred from bone level to soft tissue level. Although this surface of abutment is on the market in 2019, it is already the subject of a two-year clinical study that showed a statistically significant increase in the height of keratinized soft tissue compared to machined abutments [29,41,42]. In addition to functional benefit, its golden hue (the result of the anodyne process) is useful in supporting natural appearance in the transmucosal zone, which can be particularly relevant in cases where thin mucous or mucosal recession is present. To ensure the condition of intactness, abutments are delivered with a protective layer that dissolves after contact with the liquid, i.e. blood. This dry packaging technology stores the surfaces of the abutment hydrophilic and surface chemistry and protects it from contamination with hydrocarbon [43].

DEVELOPMENT OF IMPLANT THOUGHT IN SERBIA

With the discovery of osseointegration begins the accelerated development of implantology in the world and in our country. This is the period when the first attempts to implantation in Serbia are made. Back in 1963 Dr. Tavcar, Dr. Škokljević and Dr. Spaić at the VMA made the first attempts to implantation two subperiosteal implants in the toothless lower jaw, but after three years they were extracted. After the implant failure, skepticism reigned until 1977. The year that Dr. Skundric, Dr. Spaić and Dr. Škokljević implanted "pre-prepared wedges of a special alloy" in the form of tripods, which in the form of tripods are attached to the bone of alveolar continuation in the area of the canine and the first molar mutual. At the tips of the pegs are temporary crowns of palopont filled with silica. Encouraged by the success of the implant procedure, various implants of foreign authors, especially leafy, needle, screw-implants, are

starting to apply in the VMA. Thanks to Professors Perovic and Kosovcevic above all, implantology begins to be studied in studies at the Faculty of Dentistry in Belgrade. Soon after, in 1981 the VMA installed the first one-piece circular leaf implant in the lower jaw [44]. Like Branemark, Schroeder, Straumann and Zarb, Dr. Skundric in Serbia is parallelly developing the B.C.T. home production implant system created as a product of years of application of different systems and acquired experience. Within the B.C.T system, this innovative scientist has also incorporated a part, a mesostructure that irresistibly resembles what 30 years later one of the leading implant houses, Nobel Biocare, will promote through its concept, on-1, which marked the beginning of an era of mucointegration.

CONCLUSION

Oseointegration is one of the most critical aspects of implant success. The history of developing and improving dental implants is a magnificent and fascinating time travel. In this field of research and learning it is only possible to stop and admire man's inventiveness over the years. Materials from which dental implants were made range from gold ligature wire, clams, ivory to chromium, cobalt, to iridium and platinum. From the spiral designs of stainless steel implants to double spiral creations and endoseal root shapes, dental researchers and clinicians worked fast and hard, creating many structures to replace positions that once had natural teeth. Dental surfaces have also been modified to reduce oseointegration time. Modified surfaces include the use of hydroxyapatites, composites, carbon, glass, ceramics and titanium oxide. To make the exterior as convenient as possible, the surfaces of the implants are further sanded, oxidated, fluorised, acid-etched and modified. The latest innovative coatings are the focus of today's implant research.

Although the importance of the surface of the implant is generally known, the surface of the abutment is subjected to far less intense research. Dense soft tissue contact with the surface of the abutment can act as a barrier that protects and preserves the subcrestal bone needed to achieve healthy integration and long-term success of dental implants.

This was the driving factor in the development of the Xeal abutment surface. To

оксидоване, флуорисане, киселином, нагрисане и модификоване. Најновији иновативни премази у средишту су истраживања данашњих имплантата.

Иако је важност површине имплантата опште позната, површина абатмента је подвргнута далеко мање интензивним истраживањима. Густ контакт меког ткива са површином абатмента може деловати као баријера која штити и чува субкресталну кост потребну за постизање здраве интеграције и дугорочног успеха зубних имплантата.

ЛИТЕРАТУРА:

- Misch, Carl E. Contemporary Implant Dentistry. St. Louis, Missouri: Mosby Elsevier. 2007.
- Misch, C. E. Dental implant prosthetics (1st edition ed.). St. Louis, Missouri 63146: Elsevier MOSBY 2005.
- Pasqualini U, Pasqualini ME. Treatise of implant dentistry: The Italian Tribute to Modern Implantology, 2009; (1).
- Sullivan R M. Implant dentistry and the concept of osseointegration: A historical perspective. J of CA Dental Assoc 2001;29 (11): 737-745.
- Twin Cities Dental Implants [homepage on the Internet]. Hopkins: Twin Cities Dental Center; c2014 [cited 2015 Aug 5]. History and types of Dental Implants. Available from: <http://www.implantmn.com/about-dental-implants/history-and-types-of-dental-implants/>
- Ring M E. Pause for a moment in dental history: A thousand years of dental implants: A definitive history - Part 1. Compendium 1995;16:1060-1069.
- Riaud X. History of dental implantology. JBR Journal of Interdisciplinary Medicine and Dental Sciences. 2019;2(1): 6-7.
- Caleste M A. A Brief Historical Perspective on Dental Implants, Their Surface Coatings and Treatments. Open Dent J. 2014;16(8):50-5.
- Linkow LI, Dorfman JD. Implantology in dentistry: A brief historical perspective. N Y State Dent J. 1991;57(6):31-5.
- Kanti Pal T. Fundamentals and history of implant dentistry. J International Clinical Dent Research Org. 2015;(6):6-12.
- Vaidya P, Mahale S, Kale S, Patil A. Osseointegration- A Review. IOSR-JDMS 2017; 16(1):45-48.
- Branemark R, Branemark PI, Rydevik B, Myers RR. Osseointegration in skeletal reconstruction and rehabilitation: A review. JRRD 2001;38(2):175-81.
- Lindhe J. Clinical periodontology and Implant Dentistry. 4th edition. 2003; 809-820.
- Block S M. Dental Implants: The Last 100 Years. J Oral Maxillofac Surg. 2017;76(1):11-26.
- Leney WR. In recognition of an implant pioneer: Prof. Dr. Andre Schroeder. Int J Oral Maxillofac Implants. 1993;8(2):135-6.
- Rajan Rajput et al. A Brief Chronological Review of Dental Implant History. IDJSR. 2016;4(3):105-107.
- Albrektsson T, Jacobsson M. Bone-metal interface in osseointegration. J Prosthet Dent. 1987;57:5-10.
- Brånemark PI, Zarb GA, Albrektsson T. Chicago: Quintessence; Tissue Integrated Prostheses. 1985;201-8.
- Schroeder A, van der Zypen E, Stich H, Sutter F. The reactions of bone, connective tissue and epithelium to endosteal implants with titanium sprayed surfaces. J Maxillofac Surg. 1981;9:15-25.
- Sabane AV. Surface characteristics of dental implants: A review. J Indian Acad Dental Special. 2011;2 (2):18-21.
- Alla RK, Gijupalli K, Upadhy N, Shammam M, Rama Krishna R, Ravichandra S. Surface roughness of implants: A review. Trends Biomat Artif Org. 2011;25(3):112.
- Špadijer-Gostović A. Estetski izazovi u savremenoj stomatološkoj protetici, Beograd, 2018;79-122.
- Blaschke C, Volz U. Soft and hard tissue response to zirconium dioxide dental implants. a clinical study in man. Neuroendocrinol Lett. 2006;27(1):69-72.
- Borotić N. Uticaj različito obrađenih površina keramičkih abatenata na funkcionalnu adaptaciju mekih periimplantnih tkiva. Doktorska disertacija. 2017;5-7.
- Uike S, Gattani D and Borkar P. Soft Tissue Considerations Around Dental Implants – A Review. SF J Oral Med Dent Health 2020; 1(1):1001.
- Gibbs S, Roffel S, Meyer M, Gasser A. Biology of soft tissue repair: gingival epithelium in wound healing and attachment to the tooth and abutment surface. Eur Cell Mater. 2019;38:63-78.
- Berglundh T, Lindhe J, Ericsson I, Marinello CP, Liljenberg B, Thomsen P. The soft tissue barrier at implants and teeth. Clin Oral Implants 1991;(2):81-90.
- Al Rezk F, Trimpou G, Lauer HC, Weigl P, Krockow N. Response of soft tissue to different abutment materials with different surface topographies: a review of the literature. Gen Dent 2018;66(1):18-25.
- Hall J, Neilands J, Davies JR, et al. A randomized, controlled, clinical study on a new titanium oxide abutment surface for improved healing and soft tissue health. Clin Implant Dent Relat Res 2019;21(1):55-68.
- Nossowitz M, Teale M, Mathes S, Venturato A, Gasser A. Evaluation of anodized surfaces designed for improved soft tissue integration. Foundation for Oral Rehabilitation (FOR) 2019;1-7.
- Quirynen M, van der Mei HC, Bollen CM, Schotte A, Marechal M, Doornbusch GI, Naert I, Busscher HJ, van Steenberghe D. An in vivo study of the influence of the surface roughness of implants on the microbiology of supra- and subgingival plaque. J Dent Res 1993;72:1304-1309.
- Elter C, Heuer W, Demling A, Hannig M, Heidenblut T, Bach FW, Stiesch-Scholz M. Supra- and subgingival biofilm formation on implant abutments with different

optimize the process of muointegration, it is important to understand the surface characteristics of abutment, especially surface chemistry and nanostructure. Still the loss of

implants due to periimplantitis is a growing problem each year, so in future aspects it should be given greater importance to soft tissue health around implants.

REFERENCES:

- Misch, Carl E. Contemporary Implant Dentistry. St. Louis, Missouri: Mosby Elsevier. 2007.
- Misch, C. E. Dental implant prosthetics (1st edition ed.). St. Louis, Missouri 63146: Elsevier MOSBY 2005.
- Pasqualini U, Pasqualini ME. Treatise of implant dentistry: The Italian Tribute to Modern Implantology, 2009; (1).
- Sullivan R M. Implant dentistry and the concept of osseointegration: A historical perspective. J of CA Dental Assoc 2001;29 (11): 737-745.
- Twin Cities Dental Implants [homepage on the Internet]. Hopkins: Twin Cities Dental Center; c2014 [cited 2015 Aug 5]. History and types of Dental Implants. Available from: <http://www.implantmn.com/about-dental-implants/history-and-types-of-dental-implants/>
- Ring M E. Pause for a moment in dental history: A thousand years of dental implants: A definitive history - Part 1. Compendium 1995;16:1060-1069.
- Riaud X. History of dental implantology. JBR Journal of Interdisciplinary Medicine and Dental Sciences. 2019;2(1): 6-7.
- Caleste M A. A Brief Historical Perspective on Dental Implants, Their Surface Coatings and Treatments. Open Dent J. 2014;16(8):50-5.
- Linkow LJ, Dorfman JD. Implantology in dentistry: A brief historical perspective. N Y State Dent J. 1991;57(6):31-5.
- Kanti Pal T. Fundamentals and history of implant dentistry. J International Clinical Dent Research Org. 2015;(6):6-12.
- Vaidya P, Mahale S, Kale S, Patil A. Osseointegration- A Review. IOSR-JDMS 2017; 16(1):45-48.
- Branemark R, Branemark PI, Rydevik B, Myers RR. Osseointegration in skeletal reconstruction and rehabilitation: A review. JRRD 2001;38(2):175-81.
- Lindhe J. Clinical periodontology and Implant Dentistry. 4th edition. 2003; 809-820.
- Block S M. Dental Implants: The Last 100 Years. J Oral Maxillofac Surg. 2017;76(1):11-26.
- Leney WR. In recognition of an implant pioneer: Prof. Dr. Andre Schroeder. Int J Oral Maxillofac Implants. 1993;8(2):135-6.
- Rajan Rajput et al. A Brief Chronological Review of Dental Implant History. IDJSR. 2016;4(3):105-107.
- Albrektsson T, Jacobsson M. Bone-metal interface in osseointegration. J Prosthet Dent. 1987;57:5-10.
- Brånemark PI, Zarb GA, Albrektsson T. Chicago: Quintessence; Tissue Integrated Prostheses. 1985;201-8.
- Schroeder A, van der Zypen E, Stich H, Sutter F. The reactions of bone, connective tissue and epithelium to endosteal implants with titanium sprayed surfaces. J Maxillofac Surg. 1981;9:15-25.
- Sabane AV. Surface characteristics of dental implants: A review. J Indian Acad Dental Special. 2011;2 (2):18-21.
- Alla RK, Gijupalli K, Upadhyaya N, Shamma M, Rama Krishna R, Ravichandra S. Surface roughness of implants: A review. Trends Biomat Artif Org. 2011;25(3):112.
- Špadijer-Gostović A. Estetski izazovi u savremenoj stomatološkoj protetici, Beograd, 2018;79-122.
- Blaschke C, Volz U. Soft and hard tissue response to zirconium dioxide dental implants. a clinical study in man. Neuroendocrinol Lett. 2006;27(1):69-72.
- Borotić N. Uticaj različito obrađenih površina keramičkih abatmenata na funkcionalnu adaptaciju mekih periimplantnih tkiva. Doktorska disertacija. 2017;5-7.
- Uike S, Gattani D and Borkar P. Soft Tissue Considerations Around Dental Implants – A Review. SF J Oral Med Dent Health 2020; 1(1):1001.
- Gibbs S, Roffel S, Meyer M, Gasser A. Biology of soft tissue repair: gingival epithelium in wound healing and attachment to the tooth and abutment surface. Eur Cell Mater. 2019;38:63-78.
- Berglundh T, Lindhe J, Ericsson I, Marinello CP, Liljenberg B, Thomsen P. The soft tissue barrier at implants and teeth. Clin Oral Implants 1991;(2):81-90.
- Al Rezk F, Trimpou G, Lauer HC, Weigl P, Krockow N. Response of soft tissue to different abutment materials with different surface topographies: a review of the literature. Gen Dent 2018;66(1):18-25.
- Hall J, Neilands J, Davies JR, et al. A randomized, controlled, clinical study on a new titanium oxide abutment surface for improved healing and soft tissue health. Clin Implant Dent Relat Res 2019;21(1):55-68.
- Nosswitz M, Teale M, Mathes S, Venturato A, Gasser A. Evaluation of anodized surfaces designed for improved soft tissue integration. Foundation for Oral Rehabilitation (FOR) 2019;1-7.
- Quirynen M, van der Mei HC, Bollen CM, Schotte A, Marechal M, Doornbusch GI, Naert I, Busscher HJ, van Steenberghe D. An in vivo study of the influence of the surface roughness of implants on the microbiology of supra- and subgingival plaque. J Dent Res 1993;72:1304-1309.
- Elter C, Heuer W, Demling A, Hannig M, Heidenblut T, Bach FW, Stiesch-Scholz M. Supra- and subgingival biofilm formation on implant abutments with different surface characteristics. Int J Oral Maxillofac Implants 2008;23:327-334.
- Mendonça G, Mendonça D. B. S., Aragão F. J. L., Cooper L. F. Advancing dental implant surface technology— from micron- to nanotopography. Biomaterials. 2008;29(28):3822-3835.
- Guida L, Oliva A, Basile MA, Giordano M, Natri L, Annunziata M. Human gingival fibroblast functions are stimulated by oxidized nanostructured titanium surfaces. J Dent. 2013;41:900-907.
- Wang X, Lu T, Wen J, et al. Selective responses of human gingival fibroblasts and bacteria on carbon fiber reinforced polyetheretherketone with multilevel nanostructured TiO2. Biomaterials. 2016;83:207-218.
- Yang Y, Zhou J, Liu X, Zheng M, Yang J, Tan J. Ultraviolet light-treated zirconia with different roughness affects function of human gingival fibroblasts in vitro: The potential surface modification developed from implant to abutment. J Biomed Mater Res Part B. 2015;103B:116-124.
- Mussano F, Genova T, Laurenti M, Zicola E, Munaron L, Rivolo P, Mandracci P, Carossa S. Early response of

- surface characteristics. *Int J Oral Maxillofac Implants* 2008;23:327-334.
33. Mendonça G., Mendonça D. B. S., Aragão F. J. L., Cooper L. F. Advancing dental implant surface technology—from micron- to nanotopography. *Biomaterials*. 2008;29(28):3822–3835.
 34. Guida L, Oliva A, Basile MA, Giordano M, Nastri L, Annunziata M. Human gingival fibroblast functions are stimulated by oxidized nanostructured titanium surfaces. *J Dent*. 2013;41:900-907.
 35. Wang X, Lu T, Wen J, et al. Selective responses of human gingival fibroblasts and bacteria on carbon fiber reinforced polyetheretherketone with multilevel nanostructured TiO₂. *Biomaterials*. 2016;83:207-218.
 36. Yang Y, Zhou J, Liu X, Zheng M, Yang J, Tan J. Ultraviolet light-treated zirconia with different roughness affects function of human gingival fibroblasts in vitro: The potential surface modification developed from implant to abutment. *J Biomed Mater Res Part B*. 2015;103B:116-124.
 37. Mussano F, Genova T, Laurenti M, Zicola E, Munaron L, Rivolo P, Mandracci P, Carossa S. Early response of fibroblasts and epithelial cells to pink-shaded anodized dental implant abutments: An in vitro study. *Int J Oral Maxillofac Implants* 2018;33:571-579.
 38. Rompen E, Domken O, Degidi M, et al. The effect of material characteristics, of surface topography and of implant components and connections on soft tissue integration: a literature review. *Clin Oral Implants Res* 2006;17 (2):55-67.
 39. Att W, Hori N, Takeuchi M, Ouyang J, Yang Y, Anpo M, Ogawa T. Time-dependent degradation of titanium osteoconductivity: an implication of biological aging of implant materials. *Biomaterials*. 2009;30:5352-5363.
 40. Hori N, Att W, Ueno T, Sato N, Yamada M, Saruwatari L, Suzuki T, Ogawa T. Age-dependent degradation of the protein adsorption capacity of titanium. *J Dent Res*. 2009;88:663-667.
 41. Susin C, Finger Stadler A, Fiorini T, et al. Safety and efficacy of a novel anodized abutment on soft tissue healing in Yucatan mini-pigs. *Clin Implant Dent Relat Res* 2019;21(1):34-43.
 42. Roffel S, Wu G, Nedeljkovic I, et al. Evaluation of a novel oral mucosa in vitro implantation model for analysis of molecular interactions with dental abutment surfaces. *Clin Implant Dent Relat Res* 2019;21(1):25-33.
 43. Milleret V, Lienemann PS, Gasser A, Bauer S, Ehrbar M, Wennerberg A. Rational design and in vitro characterization of novel dental implant and abutment surfaces for balancing clinical and biological needs. *Clin Implant Dent Relat Res* 2019;21:e15-e24.
 44. Todorović IJ, Lazić Z. Razvoj implantološke misli i struke na ovim prostorima od smelih početaka do danas. *Oralna implantologija*, 2001;(2): 7-11.

- fibroblasts and epithelial cells to pink-shaded anodized dental implant abutments: An in vitro study. *Int J Oral Maxillofac Implants* 2018;33:571-579.
38. Rompen E, Domken O, Degidi M, et al. The effect of material characteristics, of surface topography and of implant components and connections on soft tissue integration: a literature review. *Clin Oral Implants Res* 2006;17 (2):55-67.
 39. Att W, Hori N, Takeuchi M, Ouyang J, Yang Y, Anpo M, Ogawa T. Time-dependent degradation of titanium osteoconductivity: an implication of biological aging of implant materials. *Biomaterials*. 2009;30:5352-5363.
 40. Hori N, Att W, Ueno T, Sato N, Yamada M, Saruwatari L, Suzuki T, Ogawa T. Age-dependent degradation of the protein adsorption capacity of titanium. *J Dent Res*. 2009;88:663-667.
 41. Susin C, Finger Stadler A, Fiorini T, et al. Safety and efficacy of a novel anodized abutment on soft tissue healing in Yucatan mini-pigs. *Clin Implant Dent Relat Res* 2019;21(1):34-43.
 42. Roffel S, Wu G, Nedeljkovic I, et al. Evaluation of a novel oral mucosa in vitro implantation model for analysis of molecular interactions with dental abutment surfaces. *Clin Implant Dent Relat Res* 2019;21(1):25-33.
 43. Milleret V, Lienemann PS, Gasser A, Bauer S, Ehrbar M, Wennerberg A. Rational design and in vitro characterization of novel dental implant and abutment surfaces for balancing clinical and biological needs. *Clin Implant Dent Relat Res* 2019;21:e15-e24.
 44. Todorović IJ, Lazić Z. Razvoj implantološke misli i struke na ovim prostorima od smelih početaka do danas. *Oralna implantologija*, 2001;(2): 7-11.