Pitting Strength Estimate for Cast Iron and Copper Alloy Materials

Edward E. Osakue

Department of Industrial Technology
Texas Southern University
Houston, Texas
USA

Lucky Anetor

Department of Engineering
Texas Southern University
Houston, Texas
USA

Kendall Harris

Provost & Vice President for Academic
Affairs
Texas Southern University
Houston, Texas
USA

An attempt is made to predict the pitting strength of cast iron and copper alloy materials from their compressive yield or compressive proof strength for a reliability of 99% at 10^7 load cycles. The compressive yield or compressive proof strength is related to the tensile strength of ductile cast iron and copper alloy materials by a proportionality factor. Two proportionality factors are used for brittle cast iron materials. The pitting strength formulation incorporates a nominal design factor at 99% reliability which is estimated from a probabilistic model based on the lognormal probability density function. Pitting strength estimates from the predictions are compared with those of American Gear Manufacturers Association (AGMA) estimates and data from other sources. The predicted values for gray cast irons had variances in the range of -11.28% to 25%. Ductile cast iron pitting strength estimates deviated from those of AGMA by -30.28% to 1.73% and 16.76% to 36.34% for Austempered ductile irons. The variances obtained for cast bronze were from 11.17% and 14.73%, but the sample size was small. These variances appear to be reasonable due to the many factors that can influence pitting resistance. Since pitting strength data for many grades of cast iron and copper alloys are not available (especially in the public domain), they may be estimated by the expressions developed in this study for initial design sizing. Also, the pitting strength of new cast iron and copper alloy materials could likewise be estimated for initial design sizing. This will eliminate long and costly contact fatigue testing at the initial design phases, which of course is necessary for design validation.

Keywords: Hertz stresses, Pitting, Friction, Rolling-sliding, Fatigue, Reliability,

1. INTRODUCTION

Pitting strength is the contact stress capability of a surface loaded repeatedly in rolling or rolling-sliding motion. Below this stress capability, failure by pitting is prevented. The pitting damage occurrence is strongly influenced by the tribological system consisting of the contacting surfaces and the lubricant. The lubricant's base oil properties and additive substances, as well as the surface roughness are the main parameters commonly considered for an improvement of the pitting load-carrying capacity of components. Nevertheless, the material strength plays a major role also in determining the pitting load-carrying capacity of components. There is common agreement that contact strength is influenced by Hertz stresses, load cycles, hardness, surface roughness, temperature, and degree of lubrication [1].

Contact fatigue which leads to pitting, results from repeated disturbance of the load pressing contacting surfaces together. Surface fatigue failure may be defined as the progressive loss of surface quality resulting from shearing and tearing away of particles from the active surface contact due to some combined rolling and sliding motions [2]. Contact fatigue process involves initiation of micro-cracks and crack propagation which can cause

permanent damage to mechanical elements when the fracture toughness of the materials is exceeded [3, 4]. Only tensile stress leads to crack growth [5]. The repeated rolling or rolling-sliding contact conditions cause permanent damage to the material due to accumulation of plastic deformation [4]. In dry contact, surface failure may consist of a flaking of oxides. In lubricated surfaces, it may occur due to direct contact of asperities when the lubricating film thickness is not sufficiently developed for complete separation of the contacting surfaces. Shearing and tearing off of large particles may be from a portion of the contact surface. Rapid deterioration of contact surfaces may occur from insufficient lubrication, or from negligence in lubrication and protection from dirt [6]. Contact fatigue is extremely important for all engineering applications involving localized contacts such as in gears, brakes, clutches, ball bearings, rolling bearings, wheels and rails, cams and followers, chain hooks and chains, screws and riveted joints [7].

Contact fatigue related failures occur after more than 10,000 load cycles and there is no endurance limit in surface fatigue [8]. Surface treatments such as carburizing or nitriding give hard surface layers that can produce good fatigue and wear resistance [9]. American Gear Manufacturers Association (AGMA) gear pitting strength data are based on tests on actual gear teeth and is determined at 99% reliability and 10^7 load cycles [1, 8] and at a temperature of 120°C and below [10]. The strengths are called nominal strength because they are modified for service or field applications using adjustment factors.

Received: January 2021, Accepted: March 2021
Correspondence to Prof. Edward E. Osakue
Department of Industrial Technology
Texas Southern University, Houston, Texas, USA
Email: edward.osakue@tsu.edu
doi:10.5937/fme2102269O

© Faculty of Mechanical Engineering, Belgrade. All rights reserved

Presently, the pitting strength of materials is determined experimentally. This is usually an expensive and time-consuming endeavor because it involves testing samples to failure [11]. The objective of this study is the prediction of the nominal pitting resistance capacity of cast iron and copper alloy materials. Osakue et al. [2] demonstrated that the pitting strength of steel materials can be related to their compressive yield strength or surface hardness. The compressive yield strength and tensile yield strength for most ductile materials are approximately the same, but are not for brittle materials. If the pitting strength of materials can be estimated from some more easily determined properties like yield strength or tensile strength, initial design may be done, and capacity performance testing can be carried out latter. This will eliminate initial experimentations for pitting strength determination, speed up product development, and reduce product cost.

2. HERTZ CONTACT MODEL

Hertz contact stress bears the name of the German physicist, Henry Hertz who first developed expressions for the stresses and deformations created when curved frictionless surfaces are statically loaded normally in 1881 [12]. Applications of Hertz theory are particularly useful in engineering for cylindrical and spherical contacts. Osakue et al. [2] showed that cylindrical contacts are more prone to pitting failure than spherical contacts. Therefore, only cylindrical contact is discussed in this study. Fig. 2a depicts the contact of two frictionless cylinders with the radii and the principal directions shown. The radius of each cylinder is in the y-z principal plane. In the x-z principal plane, the radius of each cylinder is infinite.

a) Two cylinders in contact

b) Contact pressure distribution

Fig. 2: Cylindrical contact

Fig. 2b shows the stress distribution over the contact patch along the principal directions. The concentrated normal force acts along the z-axis pressing the bodies together.

With reference to [2], the expression for the maximum contact pressure and the half-contact width may be rendered as in Eq. (1a) and eq. (1b), respectively.

$$\sigma_H = - \left[\frac{K_s F_c E_c \times 10^3}{\pi b_e \rho} \right]^{1/2} \quad a = \frac{2 K_s F_c}{\pi b_e \sigma_H} \quad (1)$$

Equation (1) has two entries and should be interpreted as Eq. (1a) and Eq. (1b) from left to right. The same rule should be applied to other equations of similar nature.

Please refer to Nomenclature for the definition of variables and parameters.

In Eq. (1a):

$$E_c = \frac{2 E_1 E_2}{E_1 (1 - \nu_2^2) + E_2 (1 - \nu_1^2)} \quad (2)$$

$$\rho = \frac{2 r_1 r_2}{r_2 \pm r_1} \quad b_e = \lambda_e b \quad (3)$$

In frictionless Hertzian contact under a static normal load, a localized complex stress state that is concentrated in a small volume of material is produced. A maximum shear stress is generated at some depth below the surface. Relative rolling motion between contacting bodies creates the same type of stress field as in static normal load but the contact patch and hence the stress field is in continuous motion. The stresses are therefore, subject to cyclic variation and the contacting surfaces are loaded in fatigue. The presence of relative sliding motion combined with rolling motion and or external tangential load, introduces tractions from frictional resistance between the contacting surfaces. The stress field is then modified and stress component values are higher than when tractive forces are not present in the contact zone. Specifically, the presence of sliding introduces a tensile stress component in the contact zone and leads to increases in contact stress component values as well as cause the location of the maximum shear stress below the contact surface to migrate upward [2, 13].

3. THEORETICAL PITTING STRENGTH

Pitting is the formation of tiny pits on surfaces of objects in rolling, or rolling-sliding motion in the presence of high contact stress. Pitting failure may originate from surface or subsurface cracks. Surface-originating pits are more prevalent than subsurface-generated cracks [14]. Surface cracks formation is facilitated by machining and grinding marks and surface flaws such as dents and scratches which when combined with geometric stress concentrations, greatly increases the possibility of surface cracks formation. Once a pit is formed, the site acts as a local stress concentration point which promotes formation of more cracks and pits.

The distortion energy (Von Mises) theory may be used to assess pitting failure when the materials in contact are ductile. Therefore, the equivalent contact stress at the surface is obtained as [15]:

$$\sigma_{eq} = \sqrt{\frac{1}{2}[(\sigma_x - \sigma_y)^2 + (\sigma_y - \sigma_z)^2 + (\sigma_z - \sigma_x)^2]} \quad (4)$$

In frictionless cylindrical contact, the equivalent surface contact stress is given by Eq. (5) [2].

$$\sigma_{eq} = \left\{ \sqrt{1-2\nu(1-\nu)} \right\} \sigma_H \quad (5)$$

Objects in Hertzian contact are often associated with vibrational impact due to local acceleration and deceleration during meshing. Therefore, yielding of their surfaces should be related to the dynamic contact yield strength which tends to be higher than the static yield strength due to higher strain rate. For low-velocity impact or light-impact, the dynamic yield strength is approximately equal to the static yield strength and the dynamic contact yield strength of ductile materials may be obtained as given in Eq. (6) [2, 16].

$$S_{yc}^* = (1.282 + 1.15\nu)S_{yc} \quad (6)$$

It may be assumed that pitting failure in a cylindrical contact occurs when the equivalent surface contact stress is at most equal to the dynamic contact yield strength as expressed in Eq. (7).

$$\sigma_{eq} = \sqrt{1-2\nu(1-\nu)}\sigma_H \leq S_{yc}^* \quad (7)$$

From Eq. (7):

$$\sigma_H \leq \frac{S_{yc}^*}{\sqrt{1-2\nu(1-\nu)}} = S_c^* \quad (8)$$

From Eq. (6) and Eq. (8):

$$S_c^* = \frac{(1.282 + 1.15\nu)S_{yc}}{\sqrt{1-2\nu(1-\nu)}} \quad (9)$$

Strain rate effect arising from impacts is ignored in Eq. (9) and applies to ductile materials. In contact problems, the state of stress is close to hydrostatic [2] which tends to increase the ductility of materials under tensile, compressive, and torsional tests. The increase has been observed not only with ductile metals but also with brittle metals and nonmetallic materials. Various brittle materials such as cast iron can deform plastically when subjected to hydrostatic pressure. The level of pressure to impact or enhanced ductility depends on the particular material [17]. Therefore, Eq. (9) should be applicable to brittle materials also, though in a more approximate sense.

The materials under consideration in this study are those of cast iron and copper alloys. Cast irons may be broadly classified into four types: gray cast iron (GCI), ductile cast iron (DCI), austempered ductile iron (ADI), and compacted graphite iron (CGI). The second letter in the acronyms stands for the type of cast iron. The most popular alloys of copper are brasses and bronzes. Brass is an alloy of copper and zinc with at least 50% copper. Bronze is an alloy of copper and tin with composition ranges of 75 to 95% for copper and about 2 to 25% for tin. Common types of brass include red, free-cutting,

cartridge and yellow brasses. Bronze types are described by the main alloying element such as aluminum, beryllium, manganese, phosphorus, lead, nickel, and silicon. Substituting Poisson's ratio values for the materials of interest from different sources [18, 19, 20] in Eq. (9) leads to Table 1.

Table 1: Theoretical Pitting Strength Prediction

Material	Poisson's Ratio	S_c^* (MPa)
Gray cast iron	0.260	$2.0157S_{yc}$
Austempered ductile iron	0.250	$1.9853S_{yc}$
Compacted graphite iron	0.260	$2.0157S_{yc}$
Ductile cast iron	0.285	$2.0914S_{yc}$
Brass	0.330	$2.2246S_{yc}$
Bronze	0.340	$2.2534S_{yc}$

4. NOMINAL PITTING STRENGTH PREDICTION

4.1 Adjustment of Theoretical Pitting Strength

The theoretical contact strength of Eq. (9) needs some modifications for practical applications. For instance, it does not account for the influence of friction which is important in real problems. Also, most strength data of materials such as yield strength, tensile strength and hardness are provided as minimum value which is unacceptable for use when failure is considered statistically [21]. Failure in contact is very close to a plane strain constrained phenomenon and should be considered too. From a reliability-based perspective, design parameters should have average or mean values and 50% reliability can be assumed for capacity models they are used in. However, higher reliability levels are usually required in practical situations. For example, AGMA gear pitting strength is assessed at 99% reliability and it is adopted as a reference in this study. Consequently, the nominal contact strength at 99% reliability for rolling-sliding motion may be expressed as:

$$S_c' = \frac{k_s k_p k_o S_c^*}{k_c n_o} \quad (9)$$

Practically, the presence of friction due to relative sliding motion in the contact zone weakens the contact strength of the material, resulting in the lowering of the theoretical contact strength. This is taken into account by the contact strength sliding factor k_s . This parameter depends on the frictional properties and lubrication conditions of the contacting materials and is better determined from experiments. From [2], $k_s = 0.80$ for bronze (phosphor) and $k_s = 0.75$ for cast iron materials. Frictional property for brass is usually not as good as that of cast iron or bronze, so k_s may be taken as 0.70 for it. Copious lubrication is assumed for the representative values stated.

The deformation of materials in Hertzian contact is constrained in at least one direction [22], very similar to plane strain deformation. The plane-strain yield strength is about 1.155 times the yield strength in uniaxial tension

[17]. This parameter is actually the ratio of the failure stress prediction from maximum shear stress theory to distortion energy theory for biaxial stress state. Thus, a plane strain factor $k_p = 1.155$ is appropriate in estimating pitting strength.

The design parameters used in the Hertz formula are average values that are associated with 50% reliability. However, higher reliability levels are usually required in practical situations; therefore, some probabilistic considerations cannot be avoided. AGMA specifies the nominal pitting strength of gear materials at a reliability of 99%. This reliability level is used to evaluate the nominal designer factor in Appendix A3 for Eq. (10) and indicated in Table 2. The parameter n_o is evaluated on the basis of the variability of design parameters and desired reliability level.

In probabilistic considerations, minimum and maximum values of design parameters are replaced with mean or average values [21]. However, most stress capability data available are given as minimum values. According to Hess et al. [23], the mean yield strength of ordinary structural steel is about 1.3 times the minimum. Therefore, $k_0 = 1.3$ is adopted in this study for all materials of interest. The parameter k_0 can be evaluated on the basis of the variability of material strength parameters and desired reliability level. If strength data available are in mean values, then the mean strength factor reduces to unity.

GCI normally contains cracks so it is not very notch sensitive [24]. The internal defects and inclusions in cast irons lead to low notch sensitivity [25]. In DCI, stress concentrations are reduced due to the presence of graphite nodules (spherical or elliptical in shape) embedded in cast iron matrix [26]. CGI has a complex coral-like graphite morphology that inhibits crack initiation and growth [19]. ADI has stabilized austenite that does not transform to brittle martensite and can undergo a strain-induced transformation when exposed to high normal forces. The transformation creates high compressive stresses in the "transformed" areas which inhibit crack formation and growth [27]. Generally, for materials permeated with internal discontinuities like cast irons, stress raisers usually have little effect, regardless of loading.

Generally, high ductility results in low notch sensitivity [28]. In the presence of ductile yielding, stress concentrations are relatively unimportant since the yielding occurs at the point of stress concentration, e.g. the tip of a notch, which merely redistributes the stresses and not necessarily lead to failure. If, however, there is only marginal ductility, or in the presence of low temperatures, then stress concentrations become more significant as the likelihood of brittle failure increases [29]. The ductility of copper alloys is in the range of 3 to 65% elongation [30]. They may be considered as having good to excellent ductility, except some that are severely strained- or aged-hardened. Some high strength alloys made by powder metallurgy can have a fracture strain of 2% and their un-notched components still exhibit yield at fracture; the fracture being of a tough ductile type [31]. Hence, it may be assumed that copper alloys are less sensitive to stress concentrations.

From the foregoing discussions, it is assumed that the surface contact stress concentration factor for cast iron

and copper alloy products is unity; that is $k_c = 1.00$ for this study. When local plastic deformation occurs near stress raisers, the stress concentration is reduced in magnitude and if a design accommodates plastic deformation, it may be reasonable to ignore stress concentration or incorporate it in a safety or design factor [31]. Table 2 is a summary of the foregoing discussions.

Table 2: Modification Factors for Theoretical Pitting Strength

Parameter	Value	Remarks
Mean strength factor	1.300	All materials
Plain strain factor	1.155	All materials
Surface stress conc. factor	1.000	All materials
Strength sliding factor	0.700	Brass
	0.755+	Cast iron
	0.800+	Bronze
Nominal design factor	1.526*	Wrought products
	1.634*	Cast products
*From Appendix A3; + Ref. [2]		

4.2 Nominal Pitting and Tensile Strengths

As mentioned before, the materials under consideration in this study are those of cast iron and copper alloys. DCI and CGI are relatively ductile and tend to have approximately equal tensile and compressive strengths. ADI is relatively ductile and GCI is brittle but they have higher compressive strength than tensile strength. The most popular alloys of copper are brasses and bronzes. Copper alloys are generally ductile and can be heat treated, strained and age hardened. These treatments give them a wide range of mechanical strength properties. They tend to have approximately equal tensile and compressive strengths.

Materials may be described as linearly-symmetric or even, when the strength in compression is approximately the same as in tension. CGI, DCI and copper alloys will be considered as even materials. Materials may be described as linearly-asymmetric or un-even, if the strengths in compression are different from that in tension. ADI and GCI will be considered as un-even materials. Strength data available are most often that for ultimate tensile strength, not the yield strength, especially for brittle materials like GCI. Therefore, it is necessary to estimate the yield strength from the tensile strength as in Eq. (11).

$$S_{yc} = \alpha_{yc} S_{uc} \quad (11)$$

For linearly-symmetric materials, then:

$$S_{uc} = S_{ut} \quad S_{yc} = \alpha_{yc} S_{ut} \quad (12)$$

In the linearly-elastic region of the stress-strain diagram, the compressive elastic modulus and tensile elastic modulus for ductile or brittle materials are approximately the same. Therefore, the offset method used on tensile strength to obtain the tensile (proof) yield strength maintains the same slope on the compression side of the stress-strain curve as it is on the tension side, so that the proportionality factors α_{yc} and α_{yt} should have the same or approximately the same value. Therefore, Eq. (12b) may be rendered as:

$$S_{yc} = \alpha_{yt} S_{ut} \quad (13)$$

Table 3: Nominal Pitting Strength Expressions for Cast Iron and Copper Alloy Materials [1, 10, 20, 31]

Material	S_c^* (MPa)	k_o	k_s	k_p	n_o	α_{yt}	α_{uc}	$S_c^/$ (MPa)
Brass –wrought	$2.2246S_{yc}$	1.30	0.700	1.155	1.526	1.000	-	$1.533S_{yt}$
Bronze-wrought	$2.2534S_{yc}$	1.30	0.800	1.155	1.526	1.000	-	$1.774S_{yt}$
Brass –cast	$2.2246S_{yc}$	1.30	0.700	1.155	1.634	0.400	1.000	$1.774S_{yt}$
Bronze-cast	$2.2534S_{yc}$	1.30	0.800	1.155	1.634	0.500	1.000	$0.828S_{ut}$
Gray cast iron	$2.0157S_{yc}$	1.30	0.755	1.155	1.634	0.563	3.386	$2.666S_{ut}$
Austempered ductile iron	$2.0157S_{yc}$	1.30	0.755	1.155	1.634	0.722	1.490	$1.482S_{ut}$
Compacted graphite iron	$2.0157S_{yc}$	1.30	0.755	1.155	1.634	0.700	1.000	$0.979S_{ut}$
Ductile cast iron	$2.0914S_{yc}$	1.30	0.755	1.155	1.634	0.736	1.000	$1.068S_{ut}$

Table 4: Nominal Pitting Strength Estimates for Some Cast Iron and Copper Alloy Materials [20, 31]

Material	Condition	Tensile Strength (MPa)	Nominal Strength, $S_c^/$ (MPa)		Deviation (%)
			<i>Published</i>	<i>Estimate</i>	
Gray cast iron	Cast	138	415 [31]	368	-11.33
	Cast	207	517 [31]	552	6.77
	Cast	276	586 [31]	736	25.60
Ductile cast iron	Annealed	414	634 [31]	442	-30.28
	Q&T*	552	634 [31]	590	-6.94
	Q&T	690	772 [31]	737	-4.53
	Q&T	827	868 [31]	883	1.73
Austempered ductile iron	Austempered	896	1138 [20] ⁺	1348	16.76
		1034	1241 [20] ⁺	1556	23.50
		1207	1345 [20] ⁺	1815	33.00
		1379	1517 [20] ⁺	2074	34.73
		1586	1724 [20] ⁺	2385	36.34
Bronze	Sand cast	276	206 [31]	229	11.17
	Heat treated	620	448 [31]	514	14.73
*Q&T: Quenched & Tempered			⁺ Allowable values		

For linearly-asymmetric materials, then:

$$S_{yc} = \alpha_{yt} S_{uc} \quad S_{uc} = \alpha_{uc} S_{ut} \quad (14)$$

$$S_{yc} = \alpha_{yt} \alpha_{uc} S_{ut} \quad (15)$$

Eq. (13) indicates that the compressive yield or compressive proof strength can be related to the tensile strength of linearly-symmetric materials by a proportionality factor α_{yt} . Similarly, Eq. (15) indicates that the compressive yield or compressive proof strength can be related to the tensile strength of linearly-asymmetric materials by two proportionality factors α_{yt} and α_{uc} . The proof strength is the yield strength that is obtained by the strain offset method which is used for materials without apparent yield point. The parameters α_{yt} and α_{uc} are not usually provided in commonly available mechanical property datasets. Therefore, effort was made to research different sources of material property data that could be analyzed to generate representative values for the parameters. Estimates of α_{yt} and α_{uc} from limited data sets are provided in Appendix A2. Table 3 summarizes the results when values are substituted into Eq. (13), Eq. (15) and Eq. (10) combined with Tables 1 and 2 for the different material types under consideration. Please note that k_c is omitted in Table 4 because of its unity value.

5. ESTIMATES OF PITTING STRENGTHS

Pitting strength data have been determined by AGMA [32] for most steel gear and some cast iron and copper alloy materials. Based on available data; comparisons with predictions from Table 3 are made in Table 4. In the table, the tensile and pitting strength data in columns 3 and 4, respectively, were obtained from different sources [1, 10, 20, 31]. The values for gray and ductile cast irons are expected maximum values. Column 5 in Table 4 contains pitting strength estimates based on expressions in Table 3. The deviations shown in column 6 of Table 4 are the percentage differences between published pitting strength and predicted data.

6. DISCUSSIONS

Eq. (9) gives the expression for the theoretical pitting strength of a material. It has two material property parameters of Poisson's ratio and the static compressive yield strength. The static compressive yield strength is used to approximate the dynamic contact strength of a material which could be influenced by strain rate during strong impact. Since light-impact is assumed in this formulation, strain rate influence is neglected. Eq. (9) is first of its kind in material and tribological technologies. Eq. (10) is the engineering approximation of the nominal pitting strength of a material. Most of the modification para-

meters can be estimated from statistical variability data, except the strength sliding factor and the plane strain factor. The plain strain factor is evaluated theoretically and the strength sliding factor can be determined experimentally for a material pair. Some experimental data [2] and engineering judgments were involved in the values used in the current analysis.

A check on the last column of Table 3 shows that the nominal pitting strength of even-cast irons (CGI and DCI) is approximately equal to their tensile strengths. The nominal pitting strength of uneven-cast iron, ADI is about 1.5 times the tensile strength and that of GCI is about 2.7 times the tensile strengths. The nominal pitting strength of cast copper alloys is lower than their tensile strengths and the nominal pitting strength of wrought copper alloys is higher than their yield strengths.

The deviations in Table 4 show that the pitting strength estimates are lower than AGMA values for low-strength (< 250 MPa) gray cast irons. Pitting strength estimate for high-strength (≥ 250 MPa) gray cast iron is higher than published data value. This situation can be explained by the fact that the average compressive strength factor for gray cast iron is lower than actual values for low-strength materials, and higher than actual values for high-strength materials. Generally, deviations for ductile cast iron indicate that the pitting strength estimates are lower than AGMA values, suggesting that the expression in Table 3 is conservative. The average deviation for ductile cast iron is -10%. An attempt was made using the yield strength for pitting strength prediction for ductile cast iron, but the results were not as good as those shown for the tensile strength. The estimates for austempered ductile iron are higher than published values which are indicated as allowable values. This means the values have been derated for design applications, so it is not too surprising to see the deviation values obtained for this material. The average deviation for austempered ductile iron is 28.87% (average is used because the values are all positive). The mechanical properties of CGI are midway of those of gray and ductile cast irons [24]. Therefore, good correlation is expected for this material, though no published data seem to be available now. The deviations for cast bronze materials are not unreasonable but the samples are too few for any definitive conclusion. Brass strength data are unavailable for comparison, but similar results as for bronze are anticipated. In all, it seems fair to say that the predicted pitting strength values in Table 4 are very good engineering estimates.

The pitting strength expressions are based on the compressive yield strength of a material, suggesting that the strength value should be for infinite load cycles. Since pitting is a wear type failure, the load cycles cannot be infinite. Now, AGMA values in Table 4 are for a load cycle of 10^7 at a reliability of 99%. Therefore, it is concluded that a load cycle of 10^7 may be assumed for the expression developed.

No correction was made for surface stress concentration because cast irons are generally notch insensitive and copper alloys are usually quite ductile. However, allowance for stress concentration may be made through a design factor which can also accommodate other types of uncertainties. Generally,

gear design procedures are not precise enough to account for the wide range of design situations [33]. Hence it is reasonable to allow for unknown factors in practice that could cause premature failure [1]. Consequently, in a design application, it is required that:

$$n_H = \frac{S_c}{\sigma_H} \geq n_c \quad S_c = S'_c Z_c \quad (36)$$

Because most of the relevant factors are already accounted for in n_o , a modest value of n_c should suffice. From Table 4, estimates for DCI and low-strength GCI are conservative, and those for copper alloys are less than 15% above AGMA values. Also, the estimate for high-strength GCI is about 25% higher; and those for ADI are about 29% on the average above published values. Therefore, the following suggestions for n_c are made:

$n_c = 1.10$ DCI materials and low-strength GCI
 $n_c = 1.15$ copper alloy materials
 $n_c = 1.30$ CGI, ADI and high-strength GCI materials
 Generally, in gearing applications, a value of 1.0 to 1.3 for n_c is common. According to Petrov et al. [34], the minimum apparent design factor may be increased by 15% for critical gear drives.

The expressions for the pitting strength of wrought copper alloys in Table 3 should be applicable to different types and grades of brass and bronze which are in common use as gear materials and in other types of applications. Estimates from these expressions should be used with caution and good engineering judgment because no published data is used here to verify their accuracy. For example, an apparent design factor of at least 1.3 may be applied in preliminary design situation when estimates are made from the expressions. However, it should be noted that workhardening effects on pitting strength is usually neglected for cast irons but may be influential for copper alloys due to their high ductility. Workhardening tends to increase pitting resistance [2].

7. CONCLUSIONS

Expressions for pitting strengths based on the tensile strength of cast iron and copper alloy materials are derived and presented in Table 3. The predicted strength values are for a reliability of 99% at 10^7 load cycles. The expressions are based on the consideration of the Hertz stress formula for line contact and when the parameters therein are treated as random variables. The probabilistic solution is based on the lognormal probability density function and is quantified in a nominal design factor. Since common property data are specified as minimum strengths and mean strength values are required in probabilistic approaches [21], correction was made through a mean strength factor for data available as minimum values. If the data available are in mean values, then the mean strength factor reduces to unity. The formulation of the expression accounts for rolling-sliding motion through a contact strength sliding factor. Consideration is also taken of the fact that Hertz contact deformation is practically a plane strain deformation since the deformed volume is usually contained. Therefore, a plane strain deformation factor is used to account for this in the formulation.

Pitting strength predictions from Table 3 are compared with those of AGMA estimates and data from [20] in Table 4. The pitting strength for low-strength gray and ductile cast irons are conservative and those for copper alloys are less than 15% above AGMA values. The estimate for high-strength GCI is about 25% higher than AGMA value, but there are not many samples for comparison. The estimates for ADI are about 29% on the average above published values. These deviations are not unreasonable. The predicted pitting strength values appear sufficiently accurate for preliminary design applications.

APPENDIX A: VARIABILITY AND DESIGN FACTOR

A1.0 CONTACT STRESS VARIABILITY

The basic capacity model expression for cylindrical Hertzian contact is Eq. (1a) or Eq. (A1).

$$\mu_H = - \left[\frac{K_s F_c}{\pi b_e} \frac{E_c \times 10^3}{\rho} \right]^{1/2} \quad (A1)$$

Assuming first order Taylor series expansion, the variability expression of Eq. (A1) is [2]:

$$\vartheta_{mH} = \sqrt{\vartheta_{ka}^2 + \vartheta_{ki}^2 + \vartheta_{Ec}^2 + \vartheta_b^2 + \vartheta_\rho^2 + \vartheta_{mc}^2} \quad (A2)$$

It may be assumed that $\vartheta_{ka} = 0.20$ and $\vartheta_{ki} = 0.10$ in this analysis [2]. The cov of Young's modulus $\vartheta_{ki} = 0.04$, $\vartheta_\rho = 0.001$, $\vartheta_b = 0.01$, and $\vartheta_{mc} = 0.05$ [2]. When values are substituted in Eq. (A8), then:

$$\vartheta_{mH} = \sqrt{0.20^2 + 0.1^2 + 0.04^2 + 0.01^2 + 0.001^2 + 0.05^2} = 0.229$$

The general miscellaneous variability is obtained as:

$$\vartheta_{ms} = \sqrt{\vartheta_{ma}^2 + \vartheta_{mf}^2 + \vartheta_{mh}^2} \quad (A3)$$

From [2]; $\vartheta_{ma} = 0.05$, $\vartheta_{mf} = 0.10$ and $\vartheta_{mh} = 0.07$.

When these values are substituted Eq. (A10):

$$\vartheta_{ms} = \sqrt{\vartheta_{ma}^2 + \vartheta_{mf}^2 + \vartheta_{mh}^2} = \sqrt{0.05^2 + 0.1^2 + 0.07^2} = 0.1319$$

The effective variability of the design capacity model is:

$$\vartheta_M = 0.5 \sqrt{\vartheta_{ms}^2 + \vartheta_{mH}^2} \quad (A4)$$

Now $\vartheta_{mH} = 0.2291$ and $\vartheta_{ms} = 0.135$, therefore:

$$\begin{aligned} \vartheta_M &= 0.5 \sqrt{\vartheta_{ms}^2 + \vartheta_{mH}^2} = \\ &= 0.5 \sqrt{0.1319^2 + 0.2291^2} = 0.1322 \end{aligned}$$

A2.0 PITTING STRENGTH VARIABILITY

In section 4.2, the compressive yield strength is correlated with the tensile strength of linearly-symmetric (even) materials by the yield strength ratio (α_{yt}) and with linearly-asymmetric (un-even) materials by α_{yt} and compressive strength factor (α_{uc}). These parameters are not usually provided in commonly available mechanical property datasets. Different sources were researched to obtain data that could be analyzed to generate representative values for the parameters. Based on GCI data in IS 2009 [35], an average value of α_{yt} was found to be 0.563 and an average value of α_{uc} was found to be 3.386. The yield strength of gray cast iron is based on 0.01% strain offset. Values were higher than the average for low-strength GCI and lower for high-strength GCI. From available data of strengths for DCI in [1, 31], an average value of α_{yt} was found to be 0.736, while that for CGI was 0.70. The sample size is 5. By analyzing ADI data in [20], an average value of α_{yt} was found to be 0.731 and an average value of α_{uc} was found to be 1.490. The sample size is 5. A search of proper data of copper alloys in [36] yielded an average value of α_{yt} equal to 0.50 for cast bronze and 0.40 for cast brass. The sample size for bronzes is 20 and that for brass is 9. Wrought copper alloys can be heat treated, strained or worked hardened, as well as age-hardened. These treatments produce a range of mechanical properties that are difficult to characterize in simple term. Table A1 gives a summary of the above analysis.

There is ample evidence of the variability of mechanical properties of materials [2]. A practical way to characterize variability is to specify the mean value and coefficient of variation (cov) for the strength data. The cov is the ratio of standard deviation to the mean of a sample. The cov of tensile yield strength for wrought steel is about 7% and for structural steel, it is about 10% [2]. The cov for wrought copper alloys with respect to yield strength will be taken as $\vartheta_{yc} = 0.10$. Cast metals have large numbers of voids in their lattices that can compromise strength in tension [37]. Dobrovolsky et al. [38, p. 45] assumed that undetected defects may reduce strength by 5 – 10% in forged parts, while they may reduce strength by 15 – 20% in cast parts. Hence cast products may exhibit up to about 10% reduction of strength compared to wrought products; or cov of about 3% to 4% increase in variability. For cast copper alloy and cast iron materials, it is assumed here that $\vartheta_{yc} = 0.13$; that is, about 3% increase in cov above wrought products. Poisson's ratio may be considered deterministic, but a cov of 0.02 [2] is suggested in critical designs. The approximations and estimation uncertainty in calculations is assumed to be associated 0.05. Table A2 summarizes the foregoing discussions.

Table A1: Yield Strength Ratios and Compressive Strength Factors for Cast Iron and Copper Alloy Materials

Material	Yield Strength Ratio	Compressive Strength Factor	Yield Strength Ratio COV (%)	Compressive Strength Factor COV (%)
Gray cast iron	0.563	3.386	3	7
Austempered cast iron	0.731	1.490		7
Compacted graphite iron	0.700	1.000		2
Ductile iron	0.736			
Cast brass	0.400			
Cast bronze	0.500			
			10	
			6	

According to Ullman [39], if the material properties are well known, use a cov of 0.05 and if the material properties are not well known, use a cov of 0.10 to 0.15. Hence the cov assumed for cast products is within suggested range.

Table A2: Cofs for Some Strength Parameters

Strength Parameters	COV
Poisson's ratio	0.02
Wrought material-yield/tensile strength	0.10
Cast material-yield/tensile strength	0.13
Miscellaneous	0.05

The variety of methods for modifying the mechanical strengths of copper alloys which include heat treatment, strain and age hardening and the multiplicity of alloy grades make it practically difficulty to correlate yield strength and tensile strength in a single factor. Therefore, using the yield strength to estimate the pitting strength appears more reasonable.

Equations (6), (13), and (15) provide functional relationships for estimating strength in terms of independent parameters. Eq. (6) may be summarized in symbolic form as in Eq. (A5a) and the cov is expressed in Eq. (A5b).

$$S'_c = f(v, S_{yc}) \quad \vartheta_C = \sqrt{\vartheta_{yc}^2 + \vartheta_v^2 + \vartheta_{mc}^2} \quad (A5)$$

When pitting strength is estimated from compressive yield strength for wrought products, then from Eq. (A14) above:

$$\vartheta_C = \sqrt{0.10^2 + 0.02^2 + 0.05^2} = 0.114$$

When pitting strength is estimated from compressive yield strength, for cast products, then from Eq. (A14) above:

$$\vartheta_C = \sqrt{0.13^2 + 0.02^2 + 0.05^2} = 0.141$$

When tensile strength data is available, then for even materials such as DCI, CGI and copper alloys; Eq. (13) is the functional strength relationship. It may be summarized in symbolic form as in Eq. (A6a) and the cov is expressed in Eq. (A6b).

$$S'_c = f(v, \alpha_{yt}, S_{ut}) \quad (A6a)$$

$$\vartheta_C = \sqrt{\vartheta_{yt}^2 + \vartheta_v^2 + \vartheta_{ut}^2 + \vartheta_{mc}^2} \quad (A6b)$$

When tensile strength data is available for wrought even materials like copper alloys:

$$\vartheta_C = \sqrt{0.03^2 + 0.02^2 + 0.10^2 + 0.05^2} = 0.118$$

When tensile strength data is available, then for even cast iron materials like DCI and CGI:

$$\vartheta_C = \sqrt{0.03^2 + 0.02^2 + 0.13^2 + 0.05^2} = 0.144$$

When tensile strength data is available, then for cast brass materials:

$$\vartheta_C = \sqrt{0.10^2 + 0.02^2 + 0.13^2 + 0.05^2} = 0.173$$

When tensile strength data is available, then for cast bronze:

$$\vartheta_C = \sqrt{0.06^2 + 0.02^2 + 0.13^2 + 0.05^2} = 0.153$$

When tensile strength data is available, then for uneven materials such as GCI, ADI; Eq. (15) is the functional strength relationship. It may be summarized in symbolic form as in Eq. (A7a) and the cov is expressed in Eq. (A7b).

$$S'_c = f(v, \alpha_{yt}, \alpha_c, S_{ut}) \quad (A7a)$$

$$\vartheta_C = \sqrt{\vartheta_{yt}^2 + \vartheta_v^2 + \vartheta_{uc}^2 + \vartheta_{ut}^2 + \vartheta_{mc}^2} \quad (A7b)$$

When tensile strength data is available, then for uneven materials such as gray cast iron and FA materials:

$$\vartheta_C = \sqrt{0.03^2 + 0.02^2 + 0.07^2 + 0.13^2 + 0.05^2} = 0.160$$

A3.0 NOMINAL DESIGN FACTOR

In the lognormal reliability-based design factor model [40], the standard deviation of a design capacity model is expressed as:

$$s_m = \sqrt{\ln[(1 + \vartheta_C^2)(1 + \vartheta_M^2)]} \quad (A8)$$

$$n_o = \exp[s_m(z + 0.5s_m)] \quad (A9)$$

The probabilistic design factor, which is also called reliability factor, is obtained as [40]:

ASTM specifies minimum strength at a reliability of 99% and the corresponding unit normal variate is $z = 2.326$. The nominal design factor is evaluated by combining Eq. (A8) and Eq. (A9), given the values of the parameters ϑ_C , ϑ_M and z . Table A3 is a summary of the evaluation of the nominal design factor for cast iron and copper alloy materials at a reliability of 99%. From the average values of the nominal design factor for wrought and cast products, cast products seem to have about 93.4% of the strength of wrought products.

Table A3: Evaluation of Nominal Design Factor at 99% Reliability

Parameter	Yield Strength		Tensile Strength				
	Wrought	Cast	Wrought	Cast			
				Even-Cast Iron	Uneven-Cast Iron	Bronze	Brass
Strength cov	0.114	0.141	0.118	0.144	0.160	0.153	0.173
Model capacity cov	0.132	0.132	0.132	0.132	0.132	0.132	0.132
Effective cov	0.174	0.192	0.176	0.195	0.206	0.201	0.216
Nominal design factor	1.522	1.592	1.529	1.604	1.650	1.629	1.692
Average nominal design factor = 1.526 for wrought products			Average nominal design factor = 1.634 for cast products				

ACKNOWLEDGEMENTS

This study was supported with funds and facilities from the College of Science, Engineering, and Technology (COSET) Research Fund and the University Faculty Development Fund of Texas Southern University, Houston, Texas. The authors are very grateful for this support.

NOMENCLATURE

ADI	austempered ductile iron
CGI	compacted graphite iron
DCI	ductile cast iron
GCI	gray cast iron
COV	coefficient of variation
HVN	hardness: Vicker's number
1,2	subscript for bodies in contact
a	radius or half-width of contact patch
B	nominal width of cylinder (mm)
b_e	effective width of cylinder (mm)
E	tensile elastic modulus
E_1	elastic modulus of material 1 (GPa)
E_2	elastic modulus of material 2 (GPa)
E_c	composite elastic modulus (GPa)
F_c	contact force (N)
k_0	minimum yield strength factor
k_s	pitting strength sliding factor
k_p	pitting strength plane strain factor
k_c	surface stress concentration factor
K_a	application overload factor
K_i	internal overload factor
K_s	service load factor
n_c	minimum apparent design factor
n_H	apparent design factor
n_0	nominal contact strength design factor at 99% reliability
r_1	radius of cylinder 1 (mm)
r_2	radius of cylinder 2 (mm)
s_m	lognormal standard deviation of design capacity model
S_c	service pitting or contact fatigue strength at 99% reliability
S_c'	nominal contact strength at 99% reliability
S_c^*	theoretical pitting strength at 50% reliability (MPa)
S_{yc}	static compressive yield strength (MPa)
S_{yc}^*	dynamic contact yield strength (MPa)
S_{ut}	ultimate tensile strength (MPa)
z	unit normal variate
Z_c	effective pitting strength modification factor
α_{yt}	yield strength ratio
ρ	composite radius of curvature (mm)
σ_H	maximum contact stress (MPa)
σ_{eq}	equivalent surface contact stress
ν	Poisson's ratio of material 1 or 2
ν_1	Poisson's ratio of material 1
ν_2	Poisson's ratio of material 2
λ_e	effective width factor
ϑ_E'	cov of E'
ϑ_E	cov of E
ϑ_{ks}	cov of K_s
ϑ_{Ec}	Cov of E_c

ϑ_b	cov of b_e
ϑ_ρ	cov of ρ
ϑ_{mc}	miscellaneous cov for approximations
ϑ_{ka}	cov of K_a
ϑ_{ki}	cov of K_i
ϑ_{ms}	cov for general miscellaneous variability
ϑ_{ma}	cov for capacity model accuracy
ϑ_{yc}	cov for compressive or tensile yield strength
ϑ_{yc}^*	cov contact yield strength
ϑ_ν	cov for Poisson's ratio
ϑ_{mf}	cov for failure model correlation with mechanical capability
ϑ_{mh}	cov for human related variability
ϑ_M	effective cov for capacity model
ϑ_C	cov for strength or mechanical capability

REFERENCES

- [1] Budynas, R. G. et al (2010), *Shigley's Mechanical Engineering Design*, 9th ed., McGraw Hill Education.
- [2] Edward E. Osakue, Anetor, L., Harris, K., *An Estimate of the Pitting Strength of Steel Materials*, FME Transactions (2021) 49, 1 -120; doi:10.5937fme 21010010.
- [3] Tu, S-T, Zhang, X-C, (2016), *Fatigue Crack Initiation Mechanisms*, Materials Science and Materials Engineering, Elsevier. Doi:10.1016/B978-0-12-803581-8.02852-6.
- [4] Šraml M., Flašker, J., (2007), *Computational Approach To Contact Fatigue Damage Initiation Analysis Of Gear Teeth Flanks*, Int J Adv Manuf Technol, (2007) 31:1066–1075; DOI 10.1007/s00170-005-0296-2
- [5] Polasik, S. J., Williams, J. J., and Chawla, N. (2001), *Fatigue Crack Initiation and Propagation in Ferrous Powder Metallurgy Alloys*, Advances in Powder Metallurgy and Particulate Materials, p. 2042-2056
- [6] Stolarski, T. A., Chap. 3: *Elements of Contact Mechanics*, Tribology in Machine Design, Butterworth-Heinemann, Oxford, 2000
- [7] Bhandari, V. B. *Design of Machine Elements*, 3rd ed., McGraw-Hill Education, New Delhi, P 142
- [8] Dudley, D. W. (2009), *Handbook of Practical Gear Design*, CRC Press, Boca Raton.
- [9] Ashby, M. F. Jones, D. R. H., (1986), *Engineering Materials 2: An Introduction to Microstructures, Processing and Design*, Pergamon Press, Oxford
- [10] Mott, R. L. (2004), *Machine Elements in Mechanical Design*, 4th ed. (SI Units), Pearson Prentice hall, New York.
- [11] Dennis P. Townsend, *Common Problems and Pitfalls in Gear Design*, NASA Technical Memorandum 88858, 1986; <https://ntrs.nasa.gov/archive/nasa/casi.ntrs.nasa.gov/19870007600.pdf>
- [12] Zahavi, E. (1992), *The Finite Element Method in Machine Design*, Prentice Hall, Englewood Cliffs, New Jersey.
- [13] Norton, R. L. (2000), *Machine Design: An Integrated Approach*, Prentice-Hall, Upper Saddle River, New Jersey, Chap. 7.

- [14] ASM Handbook, Volume 19: *Fatigue and Fracture*, ASM International, 1996
- [15] Collins, J. A. et al (2010), *Mechanical Design of Machine Elements and Machines: A Failure Prevention Perspective*, 2nd ed., John Wiley and Sons, New York, p. 864
- [16] Osakue, E. E., (1999), *A Study of Friction During Low-Velocity Impact*, Ph.D. Thesis, Department of Mechanical Engineering, University of New Brunswick, Fredericton, Canada.
- [17] Kalpankjian, S., Schmid, R. S. (2018), *Manufacturing Processes for Engineering Materials*, 6th ed. (SI ed.), Pearson (India),
- [18] Engineering Toolbox, *Poisson's Ratio*; https://www.engineeringtoolbox.com/poissons-ratio-d_1224.html
- [19] *Material Classification*; http://www.lucla.asia/2/upload/material_classification.pdf
- [20] *Austempered Ductile Iron*; <https://www.appliedprocess.com/wp-content/uploads/2018/09/2017-03-30-Typical-Properties-of-FA-in-lb-Version.pdf>
- [21] Shigley, J. E., Mischke, C. R., *Standard Handbook of Machine Design*, 2nd Edition, 1996.
- [22] *Review of Plane Stress and Plane Strain Elasticity* http://w3.uacg.bg/UACEG_site/acadstaff/userfiles/study_bg_162_L_02_Plane_Elasticity.pdf
- [23] Hess, P. E. et al (2002), *Uncertainties in Material Strength, Geometric, and Load Variables*, <http://www.assakaf.com/papers/Journals>
- [24] *Cast Iron – eFatigue*; <https://www.efatigue.com/castiron>
- [25] Noguchi, T. and Nagaoka, K., *On the Notch Strength of Cast Iron – HUSCAP*; Jan 31, 1983; https://eprints.lib.hokudai.ac.jp/dspace/bitstream/2115/41771/1/112_35-46.pdf
- [26] Mohammed, A. D., Kachit, M. *Effects of Features of Graphite Nodules on Stress Concentration in Nodular Graphite Cast Iron Material under Multi-Axial LoFang*, International Journal of Applied Engineering Research 12(5):656-663.
- [27] *Austempered Ductile Iron*; <https://www.ductile.org/didata/Section4/4intro.htm>
- [28] Kharagpur, *Module 3, Design for Strength*, Version 2 ME, IIT PTEL; <https://docplayer.net/11615428-Module-3-design-for-strength-version-2-me-iit-kharagpur.html>
- [29] Hearn, E. J, *Stress Concentration - an overview*, In *Mechanics of Materials 1* (Third Edition), 1997
- [30] *Common Material Properties*; https://www.efunda.com/materials/common_matl/
- [31] Schmid, S. R. et al. *Fundamentals of Machine Elements*, 3rd ed. CRC Press, New York.
- [32] ANSI/AGMA 2001-D04, *Fundamental Rating Factors and Calculation Methods for Involute Spur and Helical Gear Teeth*; <http://wp.kntu.ac.ir/asgari/AGMA%202001-D04.pdf>
- [33] *Introduction and Perspectives, Carburizing: Microstructures and Properties*, ASM International, 1999; www.asminternational.org
- [34] Petrov, M., Chernilevsky, D., Berezovsky, Y. (1988), *Machine Design*, MIR, Moscow.
- [35] IS 2009 Indian Standard; *Grey Iron Castings - Specification* (Fifth Revision); <http://www.iitk.ac.in/ce/test/IS-codes/is.210.2009.pdf>
- [36] Copper Alloys - Copper Development Association Inc.; www.copper.org
- [37] Ashby, M. F., Jones, D. R. H., (2012), *Engineering Materials 1: An Introduction to Properties, Applications and Design*, 4th ed. Elsevier, New York, p. 127.
- [38] Dobrovolsky, V., Zablonsky, K., Mak, S., Radchik, A., and Erlikh, L. (1965), *Machine Elements*, Foreign Language Pub. House, Moscow.
- [39] Ullman, G. D, Appendix C: *The Statistical Factor of Safety, The Mechanical Design Process*, 2nd ed., McGraw-Hill, New York, 2009.
- [40] Osakue, E. E. and Anetor, L, *A Method for Estimating a Probabilistic Design Factor*, Int'l Journal of Research in Engineering and Technology, Vol. 06, Issue 08, pp. 119 – 129, 2017.

ПРОРАЧУН ЈАЧИНЕ ПИТИНГА КОД МАТЕРИЈАЛА ОД ЛИВЕНОГ ГВОЖЂА И ЛЕГУРА БАКРА

Е.Е.Осакуе, Ј.Анетор, К.Харис

У раду је приказан покушај предвиђања јачине питинга код материјала од ливеног гвожђа и легура бакра у погледу чврстоће приноса и чврстоће на притисак за поузданост од 99% са 10^7 циклуса оптерећења. Фактор пропорционалности повезује чврстоћу приноса и чврстоћу на притисак са затезном чврстоћом материјала од нодуларног челика и легуре бакра. Два фактора пропорционалности су коришћена за материјале од кртог ливеног гвожђа. Формулација јачине питинга обједињује номинални фактор дизајна са 96% поузданости који се израчунава на основу модела вероватноће базираног на логфункцији густине вероватноће.

Прорачун јачине питинга заснован на предвиђањима упоређен је са прорачунима АГМА удружења и подацима из других извора. Предвиђене вредности за сиви лив кретале су се од -11,28% до 25%. Вредности за нодуларни лив су одступале од АГМА вредности за -30,28% до 1,73% а за нодуларни лив од 16,76% до 36,34%. Код ливене бронзе варирање је било у распону од 11,17% до 14,73% али је величина узорка била мала. Варијације код свих врста материјала се могу приписати бројним факторима који утичу на отпорност на питинг. Пошто (јавно) нису доступни подаци о јачини питинга код многих разреда ливеног гвожђа и легура бакра, они се могу израчунати на основу израза развијеног у овом раду. Јачина питинга се код наведених материјала може израчунати и код почетних одмеравања дизајна, чиме би се избегло дуготрајно и скупо испитивање замора услед контакта у почетним фазама дизајнирања, што је свакако од значаја за валидацију дизајна.