



Review paper

Mineral carbonation of industrial wastes for application in cement-based materialsSnežana Marinković^{*1)}¹⁾ Faculty of Civil Engineering, University of Belgrade, Bulevar kralja Aleksandra 73, Belgrade, Serbia ORCID 0000-0002-1808-392X*Article history*

Received: 02 July 2024

Received in revised form:

10 August 2024

Accepted: 15 August 2024

Available online: 06 September 2024

*Keywords*Accelerated carbonation,
alkaline industrial waste,
CO₂ sequestration potential,
properties of carbonated wastes,
application in cement-based materials**ABSTRACT**

Mineral carbonation is a way to permanently store carbon dioxide (CO₂) in cement-based materials. Demolished concrete waste and other types of alkaline industrial wastes, like iron and steel slags, fly ash, concrete slurry waste and cement kiln dust are prospective candidates for accelerated carbonation application. This paper presents CO₂ sequestration potentials, impacts of the accelerated carbonation on the selected properties of wastes and their possible applications in cement-based materials. Based on the analysis of published research in the area it was concluded that porosity, volume stability and heavy metals leaching of different waste types are improved after accelerated carbonation pre-treatment. This increases the effectiveness and broadness their application as substitutes for aggregates and binders in mortar and concrete. The research is however still very limited in the area of the application of the carbonated wastes with highest CO₂ sequestration potential, namely recycled concrete powders and iron/steel slags. Besides, for proper conclusions on the environmental benefits, an LCA (Life Cycle Assessment) which includes all the phases of the life cycle must be performed, which is also lacking in the published research.

1 Introduction

The carbon dioxide (CO₂) emissions have increased drastically above the period 1850-1900 and continue to increase [1], Figure 1. This is mainly a result of the unsustainable energy and land use, lifestyles and patterns of consumption and production of humans all over the planet.

Due to high concentrations of CO₂ in the atmosphere, global average surface temperature rapidly rises causing climate changes [1], Figure 1. Human-caused climate change has already resulted in rise of the sea level, decrease of Arctic sea ice, ocean acidification, greater frequency and intensity of weather and climate extremes, loss of many species, etc. [1].




Figure 1. Rise of CO₂ concentration in atmosphere and global mean temperature

* Corresponding author:

E-mail address: sneska@imk.grf.bg.ac.rs

To prevent irreversible consequences, the Intergovernmental Panel on Climate Change (IPCC) in their 2018 Special Report, titled Global Warming of 1.5°C, recommended that global average temperature increase should be limited to 1.5°C above period 1850-1900, by 2100. For that goal to be reached, it is necessary that global CO₂ emissions reach net zero by 2050, while net non-CO₂ radiative forcing (other greenhouse gas) is significantly reduced after 2030 [2].

Reaching carbon net zero in such a short time is global task that requires deep and rapid (in some cases immediate) transition in energy, land use, infrastructure (including transport and buildings), and industrial systems. Humankind faces a huge challenge, probably one of the largest ever.

As for cement and concrete industry, there are multiple pathways toward reaching net zero CO₂ emissions. They can roughly be classified into: (i) savings in clinker production [3], (ii) savings in cement and binder [4, 5], (iii) efficiency in concrete production [6-9], (iv) efficiency in design and construction [10], (v) re-carbonation (CO₂ sink) [11], and (vi) decarbonisation of electricity [3]. However, due to the high degree of process-related CO₂ emissions, cement industry is regarded as one of the rare examples where carbon capture and storage or utilisation (CCUS) technologies must be implemented since conventional mitigations levers will not suffice.


2. Carbon capture and utilization/storage CCUS

Carbon capture and storage includes the separation of CO₂ from industrial and energy-related sources, transformation into a liquid state by compression, transport to a storage location and long-term isolation from the atmosphere [12]. Permanent storage is possible only as geological storage (in geological formations, such as oil and gas fields, coal beds and deep saline formations), ocean storage (direct injection into the ocean water column or onto the deep seafloor) and mineral carbonation [12]. Figure 2 shows the plan of the first industrial-scale carbon capture and storage facility installed at a cement plant in Brewik,

Norway. The beginning of the operation is planned by the end of 2024 [13].

Captured CO₂ can be utilised in different carbon containing products, in which case it can be permanently (mineral carbonation) or temporarily stored (production of synthetic fuels, urea, methanol, etc.) [14, 15]. Carbon capture and storage is referred to as CCS and carbon capture and utilisation is referred to as CCU. In general, both pathways are together referred to as CCUS.

Mineral carbonation denotes chemical reactions in which CO₂ is converted to solid inorganic carbonates. It occurs naturally, where it is known as weathering carbonation of natural silicate rocks, such as serpentine, wollastonite and olivine, rich in magnesium oxide (MgO) and calcium oxide (CaO). The process can be accelerated using alkaline solid waste instead of natural rocks, but in both cases, it permanently stores CO₂ in the form of thermodynamically stable carbonate (CaCO₃/MgCO₃) (Eq. 1):



Since natural mineral carbonation is a very slow process, current research is oriented towards accelerated carbonation of various industrial waste such as iron/steel slags, coal and fuel combustion products (fly ash), mining/mineral processing wastes, incinerator residues, cement and concrete wastes, pulp and paper mill waste, etc. [16, 17].

2.1 CO₂ utilization in the cement and concrete industry

There are multiple ways to utilize the captured CO₂ from cement plant or any other large point source, and to store it permanently in cement and concrete products. They include CO₂ curing of concrete products at early age [18, 19, 20], injection of CO₂ in the fresh concrete mix [21, 22, 23] and mineral carbonation of different wastes. The most investigated one however, is mineral carbonation of alkali industrial waste under accelerated conditions including demolished concrete waste, concrete slurry waste, cement kiln dust, fly ash, and steel slags [24, 25, 26].




Figure 2. CCS facility at Norcem Brevik cement plant; capacity 400.000 t per year

In this work, a state-of-the-knowledge on the mineral carbonation of alkali industrial wastes is presented. Different technologies, CO₂ sequestration potentials, and possible applications in mortar and concrete production are discussed.

3. Mineral carbonation of demolished concrete waste

On average, industrial recycling of demolished concrete waste results in about 50% coarse recycled concrete aggregates CRCA, up to 40-50% fine recycled concrete aggregates FRCA (particle size <5 mm), and up to 5–10% of recycled concrete powder RCP (particle size <0.15 mm) by weight [27,28,29]. Over the past decade, a lot of research has been performed on the accelerated carbonation of recycled concrete aggregates (RCA). If exposed to accelerated carbonation, these wastes can rapidly absorb CO₂ while their properties are improved. The hydrated cement paste in residual mortar reacts with CO₂ to form CaCO₃ that fills the pores and densifies microstructure of RCA.

Due to the inferior quality of RCA compared with natural aggregate (NA), additional cement is usually required in the recycled concrete (RAC) to obtain performance similar to referent natural aggregate concrete (NAC) [30, 31]. If the properties of RCA were improved, lesser amount of added cement would be needed. Even a small reduction in cement content is important for reduction of CO₂ emissions from concrete production. At the same time, a certain amount of CO₂ is permanently stored in concrete.

Generally, accelerated carbonation can be performed in two different environments: dry (gas-solid reaction) and wet (liquid-solid reaction) conditions. In the former case, the aggregates are exposed to constant CO₂ concentration or

flow-through of CO₂ under ambient or increased temperature and pressure. In the latter case, aggregates are immersed in aqueous solution with constant flow of CO₂ injected into the solution. In dry conditions, the rate of carbonation depends on the amount of pore water in aggregate, while in wet conditions CO₂ is dissolved in the solution to form carbonate ions and carbonation reaction is not limited by CO₂ diffusion. For that reason, wet carbonation reaction is very fast under ambient pressure and temperature and can be effectively performed with gas that has low CO₂ concentration, like for instance flue gas from cement plants [32-35].

In gas-solid conditions, the efficiency of accelerated carbonation depends on the carbonation conditions and RCA properties. Carbonation conditions include CO₂ concentration and pressure, relative humidity and temperature of the environment, duration, and gas flow rate. As for properties, it depends on the water content, particle size and calcium content in RCA.

Based on extensive published research [33-43], recommendations regarding the most favorable range of mentioned influential factors are summarized in Table 1. Faster carbonation and higher CO₂ sequestration efficiency could be achieved by simultaneous adjustment of several parameters.

3.1 Coarse recycled concrete aggregates CRCA

Carbonation of CRCA leads to their properties improvement and therefore to better properties of the concrete made with CRCA. Carbonated CRCA have lower water absorption and higher density relative to non-carbonated. Figure 3 presents the improvement of water absorption due to carbonation of CRCA with particle size 5-20 mm.

Table 1. Recommended accelerated carbonation conditions and RCA properties

Parameter		Recommendation	Comment
Environmental	Relative humidity (RH)	50%-70%	Lower or higher RH values both have adverse impacts on carbonation efficiency
	CO ₂ concentration	20%-50%;	Higher concentration doesn't increase the carbonation degree, but accelerates the process
	Gas pressure	Lower than 0.5 MPa	Higher pressure doesn't significantly impact the carbonation efficiency
	Gas flow rate	Less than 5 L/min	Can achieve satisfactory carbonation efficiency with low CO ₂ flue gas (20%)
	Temperature	20-30°C	Positive effect of higher temperature but depends on many parameters; mostly used 20-30°C due to economy and uncertain impact
	Duration	Depends on conditions and particle size	Carbonation degree increases with the carbonation duration but the fastest rate is in the first several hours
RCA properties	Water content	~30% of water absorption	Easily affected by RH; water content and RH should be controlled together
	Particle size	Smaller particle size exhibits significantly higher carbonation degree	Due to much higher specific surface area and much higher residual mortar (cement paste) content
	Calcium content	Adding calcium compounds	Presoaking in CaOH ₂ solutions, waste water from ready-mixed concrete plant, etc.




Figure 3. Water absorption of CRCA (5–20 mm) before and after carbonation [43–54]

Concrete made with carbonated CRCA shows lower loss of compressive strength compared to concrete made with non-carbonated CRCA. It can be controlled within 10% of the referent NAC compressive strength even with the complete substitution of coarse natural aggregate by carbonated CRCA. Referent NAC is concrete produced with same cement content and effective w/c ratio as RAC but with natural aggregates CNCA. Figure 4 shows the ratio between compressive strength at 28 days of RAC with carbonated CRCA ($f_{cm,RAC}$) and referent NAC ($f_{cm,NAC}$), based on test results from published research. Relatively large range of published results is due to different conditions applied in accelerated carbonation: 20–100% CO_2 concentration, pressure 0.1–4 bar and duration 30 min to 72 hours.




Figure 4. Ratio between compressive strength at 28 days of RAC with carbonated CRCA ($f_{cm,RAC}$) and referent NAC ($f_{cm,NAC}$) [43, 44, 46, 47, 55–62]

As for durability related properties, the results reported on the resistance to carbonation of RAC with carbonated CRCA are contradictory. Some researchers obtained lower [56], while some obtained similar or higher carbonation resistance [37, 50] compared to that of RAC with non-carbonated CRCA. The amount of cement paste in RAC, whether with carbonated or non-carbonated CRCA, is higher than in referent NAC concrete. This has two opposite effects: a higher permeability due to higher porosity and higher amount of $CaOH_2$. The former promotes carbonation; the latter hinders it. Finally, the carbonation resistance depends on which factor of these two prevails. Cement paste in RAC with carbonated CRCA has lower porosity but lesser amount of $CaOH_2$ due to carbonation, compared to RAC with non-carbonated CRCA. Therefore, resulting performance depends on many parameters and it cannot be easily predicted. On the other hand, resistance to chloride penetration of RAC with carbonated CRCA is always improved relative to RAC with non-carbonated CRCA, due to refinement of the pore structure and total porosity reduction [34, 44, 47]. Despite the fact that mechanical and durability related properties of RAC with carbonated CRCA are improved compared to RAC with non-carbonated CRCA, they are still on average inferior to referent NAC except for the low replacement ratios, up to 25%.

3.2 Fine recycled concrete aggregates FRCA

Since the beginning of the RCA application in concrete, the use of FRCA in structural concrete was not recommended [63]. Today, despite the high availability of experimental data, there is still no consensus on its effect on the concrete properties [64–67]. FRCA contains a large amount of weak and porous mortar, consisting of mostly hydrated cement paste and sand. Reported contents of cement paste in FRCA vary widely, from 18 to 70% [63, 68–70]. High water absorption of FRCA (4–16%) causes problems both with workability and strength of concrete. The FRCA's water uptake in concrete mix is uncertain, with reported values 49–89% of its water absorption [71–74], which makes the effective w/c ratio and therefore concrete performance hardly predictable.

When carbonated, FRCA absorbs much more CO_2 than CRCA due to higher specific surface area and higher amount of attached cement paste. The reduction of water absorption of FRCA after carbonation is even more pronounced than in the CRCA case; reported range in published research is 3–60%, Figure 5. Some researchers investigated the possibility of wet instead of dry carbonation [33, 35, 83]. As already mentioned, in wet carbonation FRCA is immersed in water with controlled CO_2 concentration or flow rate. Due to the more rapid dissolution of hydrates and the fact that CO_2 diffusion is not a limiting factor in this case, the carbonation rate can be significantly increased and carbonation efficiency enhanced. Liu et al. [33] reported similar water absorption reduction after 10 minutes of wet carbonation compared to 24 hours of pressurized dry carbonation. When wet and pressurized dry carbonation of the same duration of 10 minutes were compared, Fang et al. [35] reported a 5 times higher CO_2 sequestration in wet carbonation conditions. The reason is that the wet carbonation transformed a gas-solid reaction into a liquid-solid reaction and therefore enhanced the chemical reaction rate [84, 85].




Figure 5. Water absorption of FRCA (< 5 mm) before and after carbonation [35, 41, 53, 75-83]

The negative effect of sand replacement with FRCA on concrete properties can be reduced if FRCA is pre-treated with accelerated carbonation. Moreover, recent research is focused on the full replacement of NA (both coarse and fine) with carbonated RCA.

As shown by Xiao et al. [48], with careful choice of water added to concrete mix to compensate for high water absorption values of FRCA, it was possible to produce concrete with full replacement of NA with carbonated CRCA and FRCA with similar compressive strength compared to referent NAC. In the case of RAC, the two-stage mixing method was followed [86] and the amount of additional water was set as 70% of the aggregate water absorption value minus the aggregate moisture content. Both CRCA and FRCA were obtained from real demolished concrete waste having high water absorption values, i.e. 7.67% and 13.34%, respectively. After carbonation, these values were reduced to 5.09% and 10.94%, which is still high compared to water absorption of natural aggregates (around 1%). Recycled aggregates were carbonated in chamber with a 20% CO₂ concentration and 75% relative humidity for at least 14 days (until full carbonation, which was proved by phenolphthalein test). Results of compressive strength testing showed that concrete mix with full replacement of NA with carbonated coarse and fine recycled aggregates had slightly higher compressive strength at 28 days, and slightly lower compressive strength at 180 days compared to referent NAC.

Liang et al. [76] also tested concrete mixes with full replacement of NA with carbonated and non-carbonated CRCA and FRCA. The objective was to monitor the improvement of RAC properties due to pre-treatment of recycled aggregates by accelerated carbonation. In this experiment, CRCA and FRCA were obtained by crushing and sieving the laboratory prepared mortar specimens with three different water/cement ratios equal to 0.3, 0.4 and 0.5. Recycled aggregates were carbonated in chamber with a 20% CO₂ concentration and 70% relative humidity for 10 days. Upon carbonation, water absorption of both CRCA and FRCA was reduced; for instance, from 12.3% to 8.2% and from 13.9% to 7.6% for FRCA and CRCA, respectively. It can be seen that both FRCA and CRCA had similar water

absorption because they were produced from mortar samples and had similar amount of residual mortar. Both non-carbonated and carbonated recycled aggregates were pre-saturated with extra water equal to water absorption value until a saturated surface dry state was obtained and two-stage mixing method was applied. The concrete with carbonated CRCA and FRCA showed the highest compressive strength regardless of the quality of parent mortar. Negative impact of FRCA was therefore annulated by carbonation. Results cannot be compared to referent NAC mix since it was not tested. The resistance of RAC to carbonation was significantly improved by inclusion of the carbonated recycled aggregates. Carbonation depths were measured after accelerated carbonation of concrete samples at 20 ± 3% CO₂ concentration, T = 20 ± 2°C, RH = 70 ± 5% for 56 days. Based on these results, authors calculated decrease of carbonation coefficient from 1.054 (RAC with non-carbonated RCA) to 0.63 (RAC with carbonated RCA) indicating higher resistance to carbonation. The pore structure refinement and improvement of ITZ properties prevailed over lower alkalinity of old cement paste in this experiment resulting in lower CO₂ diffusivity. Again, results cannot be compared to referent NAC mix.

Izoret et al. [57] reported results on the properties of concrete incorporating CRCA and FRCA carbonated in pilot installations implemented on a full scale in two industrial cement plants (rotating drum and fluidized bed). Authors tested several mixes with different replacement ratios of NA with carbonated and non-carbonated CRCA and FRCA with highest replacement ratio of 100% and 40% for coarse and fine aggregates, respectively. All mixes with carbonated aggregates, regardless of the replacement ratio, showed compressive strength at 28 days very similar to that of referent concrete, within 5% [57, 87]. Measurements of chloride diffusion coefficient showed no significant negative or positive impacts associated with the use of carbonated RCA compared to non-carbonated RCA; in both cases, this coefficient is higher than that of the referent concrete by 30-70%.

Chinzorigt et al. [88] tested mixes with 100% replacement of coarse NA with CRCA, and 15, 30 and 50% replacement of fine NA with carbonated and non-carbonated FRCA. Both CRCA and FRCA were obtained from commercial producer, while only FRCA was carbonated at 5% CO₂ concentration, RH 60±5%, T=20±2°C and ambient pressure for 72 hours. The loss of compressive strength at 28 days relative to referent concrete was about 10% for all replacement ratios of fine NA with carbonated FRCA. Measured carbonation depths under 56 days accelerated carbonation of all RAC were higher compared to referent concrete. Contrary to [76], in this experiment, concrete mixes with carbonated FRCA showed lower carbonation resistance relative to mixes with non-carbonated FRCA. Carbonation depth of concrete with 50% of carbonated FRCA was about 1.5 times that of referent concrete. The chloride penetration resistance was slightly lower for concrete with carbonated FRCA compared to concrete with non-carbonated FRCA despite lower porosity of the former (and both are lower than that of referent concrete). Possible explanation according to authors lies in the fact that chloride ions, which have been attached to the cement hydrate as Friedel's salt, are released into the pore solution during carbonation causing an increase of chloride ions concentration.

Ha et al. [89] compared mechanical and durability related properties of concrete with 100% replacement of both coarse and fine aggregates with carbonated CRCA and FRCA. Aggregates were carbonated for 4 and 14 days at 20% CO₂,

T= 20°C, RH=60% and ambient pressure. Measured compressive strengths at 28 days were practically same for RAC and referent NAC, i.e. full replacement of natural with carbonated recycled aggregates did not decrease the concrete compressive strength. Measured carbonation depths under 28 days accelerated carbonation were only slightly higher in concrete with carbonated RCA (9.2 mm compared to 8.6 mm in referent concrete). The same is valid for chloride diffusion coefficient: $1.47 \times 10^{-11} \text{ m}^2/\text{s}$ in concrete with carbonated RCA and $1.32 \times 10^{-11} \text{ m}^2/\text{s}$ in referent concrete.

Liang et al. [53] reported large improvement of resistance to chloride penetration of RAC with carbonated CRCA and FRCA compared to RAC with non-carbonated aggregates. Recycled aggregates were carbonated in chamber with a 20% CO₂ concentration and 70% relative humidity upon full carbonation. Authors tested mixes with full replacement of NA with carbonated and non-carbonated CRCA and FRCA and found decreased chloride permeability and steel corrosion risk in the former case (chloride diffusion coefficient reduced by 68%). Referent NAC was not tested.



Figure 6. Industrial mineral carbonation plant (two reactor containers, CO₂ storage tank and centre for the process control) [90]

Accelerated carbonation of CRCA and FRCA can be implemented at industrial scale. There are already several concrete plants in Switzerland using this approach and selling concrete containing industrially pre-carbonated recycled concrete aggregates [90], Figure 6.

3.3 Recycled concrete powder RCP

The use of recycled concrete powder in its raw form mainly causes the dilution of binder and therefore acts predominantly as filler [91, 92]. Recent research showed however, that recycled concrete powder, if carbonated, might be used as supplementary cementitious material [93, 94, 95]. Its activity as supplementary cementitious material (SCM) depends on the efficiency of separation process during recycling. If it is possible to separate the cement paste from sand and coarse aggregates, clean aggregates are obtained. On the other hand, (mostly) hydrated cement paste readily carbonates and full carbonation can be achieved in few hours under wet carbonation conditions [83-85, 96]. The material obtained in that way has high pozzolanic activity [97] and can be used as clinker replacement by 20% [98, 99] up to 40% [93]. Therefore, there are several benefits from technology – besides producing value-added products such as high quality aggregates and SCM, potentially high CO₂ reductions can be obtained through CO₂ sequestration as well as clinker amount reduction.

Technology is still at the “laboratory proof of concept” level, and no tests on concrete made with such binders were yet performed. However, some research on the level of paste and mortar properties is available [83, 94, 95]. The impact of partial replacement of ordinary Portland cement (OPC) with carbonated RCP on compressive strength of pastes and mortars, based on the published research, is shown in Figure 7. On average, replacement ratios of up to 20% are beneficial, while higher replacement ratios reduces the compressive strength of the blended paste, with the exception of the results reported in [94]. However, if the part of OPC is replaced with carbonated RCP in mortars, strength is always reduced, reduction being higher with higher replacement ratio.




Figure 7. Ratio between compressive strength at 28 days of paste and mortars with carbonated RCP ($f_{cm,OPC-RPC}$) and OPC paste and mortars ($f_{cm,OPC}$) [83, 94, 95, 98-102]

As already mentioned, for efficient separation of recycled cement pastes from aggregates, advanced recycling technologies are necessary. Several are already developed. For instance, mechanical comminution with magnetic separation [103], microwave heating [104], advanced dry recovery ADR [105, 106], Heating-Air classification System HAS [107, 108], or pure mechanical comminution by adjusting the crushing force to an intermediate one between the average compressive strengths of the aggregates and the one of the hardened cement paste - Smart Crusher [109]. Both ADR and HAS are already industrially scaled-up mobile technologies and therefore can be used for on-site recycling of demolished concrete waste. ADR can successfully produce coarse (4-16 mm) and fine (0-4 mm) fractions from wet concrete waste by crushing and using air flow for separation, Figure 8. Fine fraction is further processed with HAS in which the input is heated to a temperature of up to 1410 °C while simultaneously separating very fine particles

(0-0.25 mm) from the rest using air classification, Figure 9. Finally, the obtained 0.25-4 mm fraction is ground in a ball mill with steel balls to separate sand from activated cement paste [106, 107].

Some of presented advanced recycling processes are already applied at industrial scale, like the Smart crusher and ADR technology in the Netherlands.

3.4 CO₂ sequestration potential of demolished concrete waste

The most significant parameter that influences the potential of CO₂ sequestration is particle size of the recycled aggregate. Under same carbonation conditions, FRCA absorbs much more CO₂ than CRCA, while RCP has the highest potential, Table 2.




Figure 8. ADR recycling system [110]




Figure 9. HAC recycling system [107]

Table 2. CO₂ sequestration potential of demolished concrete waste of different particle size [42, 57, 61, 80, 111-114]

Particle size [mm]	Method	Conditions	Duration h (hour)	CO ₂ uptake [% of aggregate mass]	Ref
5-10	Gas-solid	CO ₂ conc.=100% RH=50% T=25°C Pressure =0.1/5 bar	24	2.6/2.8	[111]
10-20	Gas-solid	CO ₂ conc.=15% RH=NA T=20°C Pressure =1 bar	24	0.65-0.96	[80]
5-10	Gas-solid	CO ₂ conc.=100% RH=40-70% T=NA Pressure =0.1 bar/5bar	24	0.74/0.81	[61]
10-20	Gas-solid	CO ₂ conc.=100% RH=40-70% T=NA Pressure =0.1/5bar	24	0.65/0.66	
4-16	Gas-solid	CO ₂ conc.=20% RH=NA T=20-30°C Pressure =1 bar Fluidized bed, industry	1	1.2	[57]
4-8	Gas-solid	CO ₂ conc.=100% RH=NA, 100% WA T=NA Pressure =1 bar	1.1	0.15	[42]
1-4	Gas-solid	CO ₂ conc.=15% RH=NA T=20°C Pressure =1 bar	24	1.4/2.18/5.0 depending on the origin of the aggregate	[80]
0-4	Gas-solid	CO ₂ conc.=20% RH=NA T=20-30°C Pressure =1 bar Fluidized bed, industry	1	3.9	[57]
0-4	Gas-solid	CO ₂ conc.=100% RH=NA, 100% WA T=NA Pressure =1 bar	1.1	2.16	[42]
Median diameter 0.0168/0.0962	Liquid-solid	CO ₂ conc.=14% Solid/liquid=10g/L T=20°C Pressure =1 bar	1.5	12.0/4.0	[112]
<0.25	Liquid-solid	CO ₂ conc.=18.2% Solid/liquid=10g/L T=20°C Pressure =10 bar	0.17	5.0	[113]
<0.5	Liquid-solid	CO ₂ conc.=18.2% Solid/liquid=10g/L T=18-25°C Pressure =10 bar	0.25	11	[114]

The results in Table 2 show high variability depending on the carbonation conditions and aggregate origin, whether from laboratory concrete and paste or real demolished concrete waste. Generally, aggregates from industry have lower CO₂ uptake capacity compared to those produced in laboratory conditions, for several reasons: specific operations at recycling plants, already partially carbonated in

natural conditions, various impurities, etc. Under gas-solid conditions, results also significantly depend on the water content of recycled concrete aggregates, which mostly was not reported. The average value of CO₂ sequestration, based on this data, is 1.2%, 2.9%, and 8%, for particle size 5-20 mm, 0-4 mm and recycled concrete powder, respectively. If recycled cement paste is separated, much higher CO₂

sequestration can be obtained in liquid-solid carbonation, for instance 13.2% [115], 23% [97], 19.7-28.4% [102] (all at ambient temperature and pressure) and 28% (at elevated temperature of 80°C and pressure of 8 bar) [96]. However, these results were obtained on laboratory prepared samples (from pure cement pastes produced in laboratory), not on the hydrated cement pastes recycled in real industrial conditions.

4. Mineral carbonation of other industrial waste

Various types of industrial waste are rich in calcium and magnesium and therefore suitable for mineral CO₂ sequestration, like fly ash, steel slag, cement kiln dust, concrete slurry waste etc. Their CO₂ sequestration capacity, apart from carbonation conditions, depends mostly on the chemical composition, particle size and microstructure. A lot of research has been devoted to this subject. Carbonation under liquid-solid conditions, and at higher temperatures and pressures, was commonly used to accelerate the process [37].

Fly ash is product of combustion in coal-fired power plants. Globally, the annual production of fly ash is estimated between 0.75–1 billion tons [116]. Its chemical composition

varies a lot, depending on the type of coal from which it was obtained. Fly ash produced by combustion of bituminous coal, sub-bituminous coal, and lignite typically contains 1-12%, 5-30%, and 15-40% of CaO, respectively. It is fine material with particles ranging between < 1 – 500 μm in size and having a tri-modal particle size distribution, the bulk of which is below 75 μm [116].

Iron and steel slag is by-product from iron and steel manufacturing. High amounts of this waste is produced each year globally: 330–390 million tons of iron slag and 190–290 million tons of steel slag in 2022 [117]. It is mainly classified into four different types: blast furnace (BF) slag, oxygen furnace (BOF) slag, electric arc furnace (EAF) slag and ladle furnace (LF) slag [118]. Chemical composition of various slags differs a lot depending on the iron/steel manufacturing process [119]. In the case of iron BF slag chemical composition and particle size depend also on whether it is produced with slow cooling (air-cooled slag) or with rapid cooling (granulated slag) [120]. In any case, slag must be further grinded for application in cement or concrete, which helps also in raising the efficiency of accelerated carbonation.

Some of the published results regarding FA and slags CO₂ uptake potential are summarized in Table 3.

Table 3. CO₂ sequestration potential of demolished concrete waste of fly ash and different types of iron and steel slag [121-137]

Type of waste/ CaO content (%)	Particle size mm	Method	Conditions	CO ₂ uptake [% of aggregate mass]	Reference
FA 4.1	Median diameter d=0.04	Liquid- solid	CO ₂ conc.=100% T=30°C Pressure =10 bar Liquid/solid=10 ml/g Duration=NA	2.6	[121]
FA 7.0	Specific surface area 4.73m ² /g	Liquid- solid	CO ₂ conc.=100% T=ambient Pressure =ambient Liquid/solid=5 ml/g Duration=24 h	0.8	[122]
FA 3.4	NA	Liquid- solid	CO ₂ conc.=100% T=30°C Pressure = NA Liquid/solid=15 ml/g Duration= 15-55 min	3.2	[123]
FA 34.1	NA Petroleum coke ash	Liquid- solid	CO ₂ conc.=100% T=60°C Pressure = ambient Liquid/solid=80 ml/g Duration=16.7 h	21.0	[124]
FA 30	0.002-0.01	Liquid- solid	CO ₂ conc.=100% T=60°C Pressure = 10 bar Liquid/solid=80 ml/g Duration=1 h	26.4	[125]
FA 31.9	<0.0212	Gas- solid	CO ₂ conc.=100% T=45°C Pressure =18 bar Duration=135 min	18.2	[126]
FA 10-15	0.002-0.006	Gas- solid	CO ₂ conc.=100% T=160°C Pressure =8 bar Duration=4 h	2.3-5.3	[127]

Mineral carbonation of industrial wastes for application in cement-based materials

BF 36.6	<0.075	Liquid- solid	CO ₂ conc.=100% T=150°C Pressure =30 bar Liquid/solid=10 Duration=24h	28	[128]
BF 22.5	<0.075	Indirect	CO ₂ conc.=98% T=30°C Liquid/solid=10 Duration=60 min (NH ₄ NO ₃ , NH ₄ Cl, CH ₃ COONH ₄)	12.2	[129]
BF 47.2	<0.075	Indirect	T=25°C Pressure =1 bar Liquid/solid=10 Duration=60 min (CH ₃ COOH + EDTA)	9.0	[130]
BOF 51.1	<0.044	Liquid- solid	CO ₂ conc.=100% T=60°C Pressure =1 bar Liquid/solid=10 ml/g Duration=1 h	27.0	[131]
BOF 41.2	<0.044	Liquid- solid	CO ₂ conc.=100% T=25°C Pressure =1 bar Liquid/solid=20 ml/g Duration=2 h	28.3	[132]
BOF 46.4	<0.125	Liquid- solid	CO ₂ conc.=30% T=30°C Pressure =1 bar Liquid/solid=20 ml/g Duration=20 min	27.7	[133]
BOF 31.1	0.063-0.1	Liquid- solid	CO ₂ conc.=40% T=50°C Pressure =5 bar Liquid/solid=5 L/kg Duration=4 h	46.5	[134]
BOF 29.9	<0.15	Liquid- solid	CO ₂ conc.=100% T=100°C Pressure =10.0 MPa Liquid/solid=5 L/kg Duration=24 h	32.5	[135]
EAF 33.2	<0.024	Liquid- solid	CO ₂ conc.=18.2% T=25°C Pressure =10.68 bar Liquid/solid=10 ml/g Duration=10 min	5.2	[136]
EAF 28.3	<2.0	Liquid- solid	CO ₂ conc.=100% T=25°C Pressure =6 bar Liquid/solid=10 ml/g Duration=3 h	8.2	[137]
EAF 49.3	<0.15	Liquid- solid	CO ₂ conc.=100% T=100°C Pressure =10.0 MPa Liquid/solid=5 L/kg Duration=24 h	28	[135]

Note: BF – blast furnace slag; BOF – basic oxygen furnace slag; EAF – electric arc furnace slag

CO₂ sequestration potential of fly ash depends on the CaO content: low calcium FA has much lower CO₂ sequestration potential (0.8-3.2%) compared to high-calcium FA (18.2-26.4%). The same is valid for slags, but beside chemical composition, particle size and carbonation conditions, particularly temperature, are important factors. The smaller the particle size, the higher the CO₂ sequestration potential due to larger specific surface area. Temperature range between 50°C and 80°C seems to be optimal providing maximal CO₂ sequestration capacity [37].

Concrete slurry waste (CSW) is result of returned fresh concrete (whether over-ordered or leftovers) which is washed away from truck mixer with water. After washing, aggregates are separated from the slurry waste, which consists of very fine aggregate and cement particles and water. Usually, it is stored in sedimentation tank for a certain period to allow solids to settle and then disposed of in landfills [138]. The waste slurry can be used in wet or hardened state in various applications. If it is in hardened state, it has to be grinded and sieved before any application. The amount of produced slurry wastes is significant, up to 4.0% of freshly mixed concrete annually [25]. It is rich in CaO and can contain between 32% and 53% of CaO by mass [138-140]. Xuan et al. [138] performed a gas-solid carbonation of CSW crushed to a particles <5 mm and pre-treated to reduce the water content from 50% to 10%. Measured CO₂ sequestration after 144 hours in chamber with 100% CO₂ concentration and 0.1 bar pressure was 11%, or 110 g/kg of dry SCW. Kaliyavaradhan et al. [140] tested several carbonation conditions regarding the water-to-solid ratio (0.1, 0.25, 0.4, 0.55, 0.7) and duration time (1, 24, 72, 120, 168 hours) under same conditions: 20% CO₂ concentration, temperature 20°C and 65% RH. Dried CSW was ground and sieved to pass through 0.3 mm. The authors found that maximum CO₂ sequestration was obtained at water-to-solid ratio of 0.25 and duration of 72 h, and it was equal to 20.4 % (204.35g/kg CSW).

Cement kiln dust (CKD) is generated during the clinker production process in rotary kilns. Being a potentially hazardous waste, it is collected by air-pollution control devices. It is a fine-grained solid material, which consists of uncalcined and partially calcined raw feed, and kiln dust. Cement industry produces 30 million tons of CKD annually [141]. Typical content of CaO is between 38% and 50% [141-143] by mass. In liquid-solid carbonation tests (100% CO₂ concentration, 3 bar pressure, T=25°C and liquid-to-solid ratio=5) Medas et al. [141] measured CO₂

sequestration of 11.68% (116.8 g/kg of CKD) after 5h. Huntzinger et al. [144] measured CO₂ sequestration of 7.7% (77.0 g/kg of CKD) under ambient temperature and pressure accelerated carbonation of CKD from landfill without any pre-treatment.

Figure 10 presents the carbonation efficiency of waste materials obtained from referred published research described in previous section. It can be seen that iron and steel slags, CKD and CSW have comparable potential for mineral CO₂ sequestration (10%-30%) and that it depends not only on the CaO content, but also on the accelerated carbonation conditions and particle size. High-calcium FA (over 20% CaO by mass) belongs to that group, while low-calcium FA (below 10% CaO by mass) has small carbonation capacity.

4.1 Application

Generally these wastes, similarly to demolished concrete waste, can be applied as aggregate substitutes, Portland cement substitutes (SCM) or as fillers. If pre-treated with accelerated carbonation, their properties are improved and certain amount of CO₂ is sequestered, which both can result in the reduction of CO₂ emissions in the concrete life cycle.

As aggregates

Carbonated iron and steel slag can be used as a substitute for natural fine and coarse aggregates in mortars and concrete. Beside the significant CO₂ sequestration potential, accelerated carbonation pre-treatment increases the volume stability, reduces the leaching of heavy metals and improves slag mechanical properties [145-147]. Pang et al. [148, 149] tested the impact of partial replacement of fine and coarse natural aggregate with carbonated BOF slag on concrete properties, keeping same w/c and cement content in the concrete mix. The authors reported similar workability despite higher WA, 20% higher compressive strength at 28 days, improved ITZ zone properties, significantly higher freeze-thaw resistance (2-3 times) compared to reference samples with only natural aggregates. However, production of carbonated fine and coarse slag aggregates included grinding, pelletization, carbonation at 70°C and pressure of 3 bar, and crushing again, which all required a significant energy. Bodor et al. [150] tested the properties of cement mortar with 50% of natural sand aggregate replaced by carbonated BOF slag. Carbonation was conducted in liquid-




Figure 10. CO₂ sequestration potential of FA, iron and steel slags, CSW and CKD [121-135, 138, 140, 141, 144]

solid conditions at 90 °C and 20 bar CO₂ pressure, for 2 h duration. Mortar mixtures prepared with carbonated BOF slag of <0.5 mm particle size showed similar consistency via flow table test, compressive strength and leaching of toxic elements to referent mortar mixture with only natural sand. In this case, only treatment of slag prior to carbonation was crushing and sieving, while CO₂ sequestration equal to 11-19% was obtained.

Several other works showed the applicability of carbonated steel slags as aggregates for concrete: artificial aggregates obtained by wet granulation process of BOF powder [151] or a combination of slag, fly ash and cement [152]. Shen et al. [153] used original slag as coarse aggregate and ball-milled original slag as powder in production of carbonated steel slag pervious concrete. Although commonly tested concrete property – compressive strength – was obtained similar to referent concrete prepared with natural aggregate, it should be kept in mind that significant pre-treatment operations can annul (cancel) the benefits from sequestered CO₂ and waste reduction [154].

As SCM

Ground granulated BF slag (GGBS) and FA are already used as clinker replacement in commercial cements. Research on utilization of carbonated slag and fly ash as SCM is limited so far. Ebrahimi et al. [123] and Pei et al. [155] reported that up to 10% replacement of clinker with carbonated FA did not impair the compressive strength of blended cement pastes. Sahoo et al. [156] investigated concrete with 25% cement replacement with carbonated fly ash and reported high resistance against salt, sulfate and acid attack. Regarding carbonated slag as SCM, Chen et al. [157] and Pan et al. [158] reported similar results – up to 10% replacement with carbonated slags provided similar compressive strengths to pure OPC pastes and mortars, while maintaining high volume stability. The volume stability of cementitious materials containing slag is usually a problem, but carbonation consumes the expansion phase in slag (CaO) and improves it effectively. For both fly ash and slag, the main result of carbonation reaction is fine calcite (CaCO₃) which fills the pores and reduces pastes and mortars porosity, or becomes nucleus for hydration contributing to strength gain (setting time decrease) of cement pastes and mortars [155, 157, 159].

Utilization of ground but non-carbonated concrete slurry waste and cement kiln dust as SCMs was investigated in the previous research. Replacing clinker with CSW and CKD reduces mechanical and durability related properties of mortars and concretes, and general conclusion is that replacement should be limited to 10% to achieve similar strengths and durability of OPC mortars and concretes [28, 160]. Carbonated CSW and CKD should however improve the mortar and concrete performance due to same reasons as in the case of carbonated FA and slag. Kaliyavaradhan et al. [140] for instance, reported higher strength of mortar prepared with carbonated CSW compared to mortar prepared with fresh CSW, at 20% cement replacement ratio. As concluded by the authors, strength improvement was probably result of the reaction of aluminat C3A and calcite to form calcium carboaluminate hydrate. However, it was still slightly lower compared to pure OPC mortar. Sharma et al. [143] investigated carbonation curing of mortars containing CKD, while Xuan et al. [138] studied the carbonation curing of partition wall blocks made of CSW and fine recycled concrete aggregates. In these cases, accelerated carbonation was applied on the final product resulting in the improvement of their performance.

5. Conclusion

Mineral carbonation of alkaline industrial waste is a way to permanently store CO₂ in cement-based materials. On the other hand, pre-treatment with accelerated carbonation improves properties of various wastes enabling in that way their application as substitutes for natural aggregates and OPC.

Accelerated carbonation of coarse and fine aggregates obtained by demolished concrete waste leads to decrease of their porosity due to formation of calcite, which fill in the pores and densify the microstructure. Most of the experimental research showed that full replacement of natural aggregates with carbonated ones didn't jeopardize the compressive strength of RAC, meaning that there is no need to increase the cement content to obtain strength similar to that of the referent NAC. As for carbonation and chloride penetration resistance of RAC with carbonated aggregates, different results were reported indicating that those concretes, despite lower permeability, may have lower resistances compared to referent NAC. This may be because of lower alkalinity of their pastes in the carbonation resistance case, or due to increased chloride concentration as a consequence of previous carbonation of aggregates in the chloride penetration resistance case. CO₂ sequestration potential depends mostly on the particle size and water content of aggregates under same carbonation conditions: FRCA can absorb up to 5% of their weight depending on the water content, while CO₂ uptake potential of CRCA is modest, 1-2% of their weight. Recycled concrete powder has much higher CO₂ sequestration potential ranging from 5-11% and in the case of pure recycled cement paste reaches 30% of the weight. Carbonated RCP has good pozzolanic activity and can be used as SCM. In the amounts of up to 20% it even increases the strength of paste, while for higher replacement ratios, the strength is decreased.

Similar to demolished concrete waste, the properties of fly ash, slags, cement kiln dust and concrete slurry waste are improved when pre-treated with accelerated carbonation, including higher volume stability and lower leaching of heavy metals. Except for low-calcium FA, these wastes have high CO₂ sequestration potential, between 10% and 30% of their weight, especially iron and steel slags. Carbonated slags can be used as substitute for aggregates, and when ground into powder they can be used as SCM, as well as carbonated FA, CKD and CSW. However, research on the impact of such aggregates and binders on the concrete performance doesn't exist at the moment. The same is valid for the carbonated RCP utilization as partial replacement of OPC in concrete.

Despite the obvious benefits of the mineral carbonation technology, one should kept in mind that these benefits could easily be cancelled by required energy and CO₂ emissions during process. Beside the accelerated carbonation itself (energy requirement depends on the applied pressure and temperature), some pre-treatment processes are energy intensive, like drying of recycled aggregates for instance. Wet aggregates are common industrial condition and such high water content practically disables carbonation – so, they must be dried. Preparation of slags for application as aggregates or SCM include various pre-treatments beside accelerated carbonation. Therefore, for proper conclusions on environmental benefits of mineral carbonation application in cement-based materials, an LCA (Life Cycle Assessment) which includes all the phases of the life cycle must be performed.

Regarding CO₂ sequestration potential, most promising candidates for mineral carbonation are recycled concrete powders, iron and steel slags, and high-calcium fly ash. The future research should be oriented towards better understanding of the impact of their application as aggregates or SCM in cement based materials, concrete most of all.

CRediT authorship contribution statement

Snežana Marinković: Conceptualization; Methodology; Data curation; Formal analysis; Writing.

Declaration of competing interest

Author declares no conflict of interest.

Acknowledgments

Research was not supported by other persons or institutions.

References

- [1] IPCC, 2023: Climate Change 2023: Synthesis Report. Contribution of Working Groups I, II and III to the Sixth Assessment Report of the Intergovernmental Panel on Climate Change [Core Writing Team, H. Lee and J. Romero (eds.)]. IPCC, Geneva, Switzerland, 184 pp., doi: 10.59327/IPCC/AR6-9789291691647
- [2] IPCC, 2018: Global Warming of 1.5°C. An IPCC Special Report on the impacts of global warming of 1.5°C above pre-industrial levels and related global greenhouse gas emission pathways, in the context of strengthening the global response to the threat of climate change, sustainable development, and efforts to eradicate poverty [Masson-Delmotte, V., P. Zhai, H.-O. Pörtner, D. Roberts, J. Skea, P.R. Shukla, A. Pirani, W. Moufouma-Okia, C. Péan, R. Pidcock, S. Connors, J.B.R. Matthews, Y. Chen, X. Zhou, M.I. Gomis, E. Lonnoy, T. Maycock, M. Tignor, and T. Waterfield (eds.)],
- [3] GCCA. Concrete Future – The GCCA 2050 Cement and Concrete Industry Roadmap for Net Zero Concrete, 2021. Available at: <https://gccassociation.org/concretefuture/>
- [4] G. Habert, S.A. Miller, V.M. John et al., Environmental impacts and decarbonization strategies in the cement and concrete industries. *Nature Reviews Earth & Environment*, 1 (11), 2020, 559-573. <https://doi.org/10.1038/s43017-020-0093-3>
- [5] K. Scrivener, F. Martirena, S. Bishnoi, S. Maity, Calcined clay limestone cements (LC³), *Cement and Concrete Research* 114, 2018, 49–56. <https://doi.org/10.1016/j.cemconres.2017.08.017>
- [6] A. Passer, R. Deutsch, M. Scherz, *Beton-LCA – Wie grün ist grau?*. Baukongress, 63-64, 2018.
- [7] W. Shanks, C.F. Dunant, M.P. Drewniok, R.C. Lupton, A. Serrenho, J.M. Allwood, How much cement can we do without? Lessons from cement material flows in the UK, *Resources, Conservation & Recycling* 141, 2019, 441–454. <https://doi.org/10.1016/j.resconrec.2018.11.002>
- [8] M. Marinković, A. Radović, V. Carević, Carbonation of limestone powder concrete: state-of-the-art overview, *Building Materials and Structures* 66, 2023, 2300005M. <https://doi.org/10.5937/GRMK2300005M>
- [9] J. Dragaš, S. Marinković, V. Radonjanin, Prediction models for high-volume fly ash concrete practical application: mechanical properties and experimental database, *Building Materials and Structures* 64, 2021, 19-43. <https://doi.org/10.5937/GRMK2101019D>
- [10] H. Hafez, P. Bajić, S. Aidarov, X. Malija, M. Drewniok, P. Purnell, N. Tošić, Parametric study on the decarbonization potential of structural system and concrete mix design choices for mid-rise concrete buildings, *Materials and Structures* 57, 2024, 85. <https://doi.org/10.1617/s11527-024-02367-1>
- [11] H. Stripple, C. Ljungkrantz, T. Gustafsson, R. Andersson, CO₂ uptake in cement-containing products, IVL Swedish Environmental Research Institute, Stockholm, Sweden, 2018.
- [12] IPCC, 2005: IPCC Special Report on Carbon Dioxide Capture and Storage. Prepared by Working Group III of the Intergovernmental Panel on Climate Change [Metz, B., O. Davidson, H. C. de Coninck, M. Loos, and L. A. Meyer (eds.)]. Cambridge University Press, Cambridge, United Kingdom and New York, NY, USA, 442 pp.
- [13] Heidelberg Materials, Annual and Sustainability Report 2023, available at www.heidelbergmaterials.com
- [14] J. Patricio, A. Angelis-Dimakis, A. Castillo-Castillo, Y. Kalmykova, L. Rosado, Region prioritization for the development of carbon capture and utilization technologies, *Journal of CO₂ Utilization* 17 (2017) 50–59, <http://dx.doi.org/10.1016/j.jcou.2016.10.002>
- [15] C. Schmid, A. Hahn, Potential CO₂ utilisation in Germany: An analysis of theoretical CO₂ demand by 2030, *Journal of CO₂ Utilization* 50 (2021) 101580, <https://doi.org/10.1016/j.jcou.2021.101580>
- [16] H. Ostovari, A. Sternberg, A. Bardow, Rock 'n' use of CO₂: carbon footprint of carbon capture and utilization by mineralization, *Sustainable Energy Fuels* 4 (2020) 4482–4496, DOI: 10.1039/d0se00190b
- [17] B. Robertson, M. Mousavian, *The Carbon Capture Crux Lessons Learned*, Institute for Energy Economics and Financial Analysis (IEEFA) report, 2022, 79 pp.
- [18] Y. Shao, A. Z. Morshed, Early carbonation for hollow-core concrete slab curing and carbon dioxide recycling, *Materials and Structures* (2015) 48:307–319, DOI 10.1617/s11527-013-0185-3
- [19] V. Rostami, Y. Shao, A. J. Boyd, Carbonation Curing versus Steam Curing for Precast Concrete Production, *J. Mater. Civ. Eng.*, 2012, 24(9): 1221-1229, DOI:10.1061/(ASCE)MT.1943-5533.0000462
- [20] D. Zhang, Y. Shao, Early age carbonation curing for precast reinforced concretes, *Construction and Building Materials* 113 (2016) 134–143, <http://dx.doi.org/10.1016/j.conbuildmat.2016.03.048>
- [21] S. Monkman, M. MacDonald, On carbon dioxide utilization as a means to improve the sustainability of ready-mixed concrete, *Journal of Cleaner Production* 167 (2017) 365e375, <http://dx.doi.org/10.1016/j.jclepro.2017.08.194>
- [22] Z. He, Z. Li, Y. Shao, Effect of Carbonation Mixing on CO₂ Uptake and Strength Gain in Concrete, *J. Mater. Civ. Eng.*, 2017, 29(10): 04017176, DOI: 10.1061/(ASCE)MT.1943-5533.0002031.
- [23] A. Hosseinpanahi, L. Shen, P. Dera, R. Mirmoghtadaei, Properties and microstructure of concrete and cementitious paste with liquid carbon dioxide additives, *Journal of Cleaner Production* 414 (2023) 137293, <https://doi.org/10.1016/j.jclepro.2023.137293>

- [24] M. Hanifa, R. Agarwal, U. Sharma, P.C. Thapliyal, L.P. Singh, A review on CO₂ capture and sequestration in the construction industry: Emerging approaches and commercialised technologies, *Journal of CO₂ Utilization* 67 (2023) 102292, <https://doi.org/10.1016/j.jcou.2022.102292>
- [25] M. Kazemian, B. Shafei, Carbon sequestration and storage in concrete: A state-of-the-art review of compositions, methods, and developments, *Journal of CO₂ Utilization* 70 (2023) 102443, <https://doi.org/10.1016/j.jcou.2023.102443>
- [26] N. Li, L. Mo, C. Unluer, Emerging CO₂ utilization technologies for construction materials: A review, *Journal of CO₂ Utilization* 65 (2022) 102237, <https://doi.org/10.1016/j.jcou.2022.102237>
- [27] Y.A. Villagrán-Zaccardi, A.T.M. Marsh, M.E. Sosa, C.J. Zega, N. De Belie, S.A. Bernal, Complete re-utilization of waste concretes—Valorisation pathways and research needs, *Resources, Conservation & Recycling* 177 (2022) 105955, <https://doi.org/10.1016/j.resconrec.2021.105955>
- [28] S.K. Kaliyavaradhan, T.-C. Ling, K.H. Mo, Valorization of waste powders from cement-concrete life cycle: A pathway to circular future, *Journal of Cleaner Production* 268 (2020) 122358, <https://doi.org/10.1016/j.jclepro.2020.122358>
- [29] J. Schoon, K. De Buysser, I. Van Driessche, N. De Belie, Fines extracted from recycled concrete as alternative raw material for Portland cement clinker production, *Cement & Concrete Composites* 58 (2015) 70–80, <http://dx.doi.org/10.1016/j.cemconcomp.2015.01.003>
- [30] S. Marinković, V. Carević, Comparative studies of the life cycle analysis between conventional and recycled aggregate concrete, in De Brito J. and Agrelá F. (eds.): *New Trends in Eco-Efficient and Recycled Concrete*, Elsevier Ltd. Woodhead Publishing, 2019, p. 257–291, <https://doi.org/10.1016/B978-0-08-102480-5.00010-5>
- [31] S. Marinković, I. Josa, S. Braymand, N. Tošić, Sustainability assessment of recycled aggregate concrete structures: A critical view on the current state-of-knowledge and practice, *Structural Concrete* 24(2) (2023) 1956–1979, <https://doi.org/10.1002/suco.202201245>
- [32] D. Meng, C. Unluer, E.-H. Yang, S. Qian, Carbon sequestration and utilization in cement-based materials and potential impacts on durability of structural concrete, *Construction and Building Materials* 361 (2022) 129610, <https://doi.org/10.1016/j.conbuildmat.2022.129610>
- [33] S. Liu, P. Shen, D. Xuan, L. Li, A. Sojobi, B. Zhan, C.S. Poon, A comparison of liquid-solid and gas-solid accelerated carbonation for enhancement of recycled concrete aggregate, *Cement and Concrete Composites* 118 (2021) 103988, <https://doi.org/10.1016/j.cemconcomp.2021.103988>
- [34] Y. Pu, L. Li, X. Shi, Q. Wang, A. Abomohra, Recent advances in accelerated carbonation for improving cement-based materials and CO₂ mitigation from a life cycle perspective, *Construction and Building Materials* 388 (2023) 131695, <https://doi.org/10.1016/j.conbuildmat.2023.131695>
- [35] X. Fang, D. Xuan, P. Shen, C.S. Poon, Fast enhancement of recycled fine aggregates properties by wet carbonation, *Journal of Cleaner Production* 313 (2021) 127867, <https://doi.org/10.1016/j.jclepro.2021.127867>
- [36] Y. Pu, L. Li, Q. Wang, X. Shi, C. Luan, G. Zhang, L. Fu, A.E.-F. Abomohra, Accelerated carbonation technology for enhanced treatment of recycled concrete aggregates: A state-of-the-art review, *Construction and Building Materials* 282 (2021) 2671, <https://doi.org/10.1016/j.conbuildmat.2021.122671>
- [37] L. Li, M. Wu, An overview of utilizing CO₂ for accelerated carbonation treatment in the concrete industry, *Journal of CO₂ Utilization* 60 (2022) 102000, <https://doi.org/10.1016/j.jcou.2022.102000>
- [38] C. Liang, B. Pan, Z. Ma, Z. He, Z. Duan, Utilization of CO₂ curing to enhance the properties of recycled aggregate and prepared concrete: A review, *Cement and Concrete Composites* 105 (2020) 103446, <https://doi.org/10.1016/j.cemconcomp.2019.103446>
- [39] K. Liu, W. Xu, D. Sun, J. Tang, A. Wang, D. Chen, Carbonation of recycled aggregate and its effect on properties of recycled aggregate concrete: A review, *Mater. Express*, Vol. 11, No. 9, 2021, doi:10.1166/mex.2021.2045
- [40] D. Wang, J. Xiao, Z. Duan, Strategies to accelerate CO₂ sequestration of cement-based materials and their application prospects, *Construction and Building Materials* 314 (2022) 125646, <https://doi.org/10.1016/j.conbuildmat.2021.125646>
- [41] G.S. dos Reis, B.G. Cazacliu, R. Artoni, J.-m. Torrenti, Effect of the accelerated carbonation treatment on the recycled sand physicochemical characteristics through the rolling carbonation process, *Journal of CO₂ Utilization* 39 (2020) 101181, <https://doi.org/10.1016/j.jcou.2020.101181>
- [42] A. Leemann, F. Winnefeld, B. Münch, J. Tiefenthaler, Accelerated carbonation of recycled concrete aggregates and its implications for the production of recycling concrete, *Journal of Building Engineering* 79 (2023) 107779, <https://doi.org/10.1016/j.jobe.2023.107779>
- [43] Y. Pu, L. Li, Q. Wang, X. Shi, L. Fu, G. Zhang, C. Luan, A.E.-F. Abomohra, Accelerated carbonation treatment of recycled concrete aggregates using flue gas: A comparative study towards performance improvement, *Journal of CO₂ Utilization* 43 (2021) 101362, <https://doi.org/10.1016/j.jcou.2020.101362>
- [44] X. Fang, B. Zhan, C.S. Poon, Enhancement of recycled aggregates and concrete by combined treatment of spraying Ca²⁺ rich wastewater and flow-through carbonation, *Constr. Build. Mater.* 277 (2021), 122202, <https://doi.org/10.1016/j.conbuildmat.2020.122202>
- [45] Y. Li, S. Zhang, R. Wang, Y. Zhao, C. Men, Effects of carbonation treatment on the crushing characteristics of recycled coarse aggregates, *Constr. Build. Mater.* 201 (2019) 408–420, <https://doi.org/10.1016/j.conbuildmat.2018.12.158>
- [46] B. Lu, C. Shi, Z. Cao, M. Guo, J. Zheng, Effect of carbonated coarse recycled concrete aggregate on the properties and microstructure of recycled concrete, *J. Clean. Prod.* 233 (2019) 421–428, <https://doi.org/10.1016/j.jclepro.2019.05.350>
- [47] S. Luo, S. Ye, J. Xiao, J. Zheng, Y. Zhu, Carbonated recycled coarse aggregate and uniaxial compressive stress-strain relation of recycled aggregate concrete, *Constr. Build. Mater.* 188 (2018) 956–965, <https://doi.org/10.1016/j.conbuildmat.2018.08.159>
- [48] J. Xiao, H. Zhang, Y. Tang, Q. Deng, D. Wang, C.-s. Poon, Fully utilizing carbonated recycled aggregates in concrete: strength, drying shrinkage and carbon

- emissions analysis, *J. Clean. Prod.* 377 (2022), 134520, <https://doi.org/10.1016/j.jclepro.2022.134520>
- [49] B. Tang, M. Fan, Z. Yang, Y. Sun, L. Yuan, A comparison study of aggregate carbonation and concrete carbonation for the enhancement of recycled aggregate pervious concrete, *Construction and Building Materials* 371 (2023) 130797, <https://doi.org/10.1016/j.conbuildmat.2023.130797>
- [50] D. Xuan, B. Zhan, C.S. Poon, Durability of recycled aggregate concrete prepared with carbonated recycled concrete aggregates, *Cement and Concrete Composites* 84 (2017) 214–221, <https://doi.org/10.1016/j.cemconcomp.2017.09.015>
- [51] A.H. Zadeh, M. Mamirov, S. Kim, J. Hu, CO₂-treatment of recycled concrete aggregates to improve mechanical and environmental properties for unbound applications, *Construction and Building Materials* 275 (2021) 122180, <https://doi.org/10.1016/j.conbuildmat.2020.122180>
- [52] B. Zhan, D. Xuan, W. Zenga, C.S. Poon, Carbonation treatment of recycled concrete aggregate: Effect on transport properties and steel corrosion of recycled aggregate concrete, *Cement and Concrete Composites* 104 (2019) 103360, <https://doi.org/10.1016/j.cemconcomp.2019.103360>
- [53] C. Liang, H. Ma, Y. Pan, Z. Ma, Z. Duan, Z. He, Chloride permeability and the caused steel corrosion in the concrete with carbonated recycled aggregate, *Constr. Build. Mater.* 218 (2019) 506–518, <https://doi.org/10.1016/j.conbuildmat.2019.05.136>
- [54] B. Zhan, C.S. Poon, Q. Liu, S. Kou, C. Shi, Experimental study on CO₂ curing for enhancement of recycled aggregate properties, *Construction and Building Materials* 67 (2014) 3–7, <http://dx.doi.org/10.1016/j.conbuildmat.2013.09.008>
- [55] S. Kou, B. Zhan, C.S. Poon, Use of a CO₂ curing step to improve the properties of concrete prepared with recycled aggregates, *Cement & Concrete Composites* 45 (2014) 22–28, <http://dx.doi.org/10.1016/j.cemconcomp.2013.09.008>
- [56] M. Etxebarria, S. Castillo, How the Carbonation Treatment of Different Types of Recycled Aggregates Affects the Properties of Concrete, *Sustainability* 2023, 15, 3169, <https://doi.org/10.3390/su15043169>
- [57] L. Izoret, T. Pernin, J.-M. Potier, J.-M. Torrenti, Impact of Industrial Application of Fast Carbonation of Recycled Concrete Aggregates, *Appl. Sci.* 2023, 13, 849, <https://doi.org/10.3390/app13020849>
- [58] S.M.S. Kazmi, M.J. Munir, Y.-F. Wua, I.P.Y. Zhou, F. Xing, Effect of recycled aggregate treatment techniques on the durability of concrete: A comparative evaluation, *Construction and Building Materials* 264 (2020) 120284, <https://doi.org/10.1016/j.conbuildmat.2020.120284>
- [59] N. Russo, F. Lollini, Effect of carbonated recycled coarse aggregates on the mechanical and durability properties of concrete, *Journal of Building Engineering* 51 (2022) 104290, <https://doi.org/10.1016/j.jobe.2022.104290>
- [60] H. Sharma, D.K. Ashish, S.K. Sharma, Development of low-carbon recycled aggregate concrete using carbonation treatment and alccofine, *Energy, Ecology and Environment* 2023, <https://doi.org/10.1007/s40974-023-00299-0>
- [61] D. Xuan, B. Zhan, C.S. Poon, Assessment of mechanical properties of concrete incorporating carbonated recycled concrete aggregates, *Cement and Concrete Composites* 65 (2016) 67–74, <http://dx.doi.org/10.1016/j.cemconcomp.2015.10.018>
- [62] V.W.Y. Tam, A. Butera, K.N. Le, Carbon-conditioned recycled aggregate in concrete production, *Journal of Cleaner Production* 133 (2016) 672–680, <http://dx.doi.org/10.1016/j.jclepro.2016.06.007>
- [63] T.C. Hansen, Recycled aggregates and recycled aggregate concrete second state-of-the-art report developments 1945–1985, *Materials and Structures* 19, 201–246, <http://dx.doi.org/10.1007/BF02472036>
- [64] L. Evangelista, J. de Brito, Durability of crushed fine recycled aggregate concrete assessed by permeability-related properties, *Magazine of Concrete Research* 71, 1142–1150, <https://doi.org/10.1680/jmacr.18.00093>
- [65] G. Punte de Andrade, G. de Castro Polisseni, M. Pepe, R.D.T. Filho, Design of structural concrete mixtures containing fine recycled concrete aggregate using packing model, *Construction and Building Materials* 252 (2020) 119091, <https://doi.org/10.1016/j.conbuildmat.2020.119091>
- [66] L. Yu, L. Huang, H. Ding, Rheological and mechanical properties of ultra-high-performance concrete containing fine recycled concrete aggregates, *Materials* 12, 3717, <https://doi.org/10.3390/ma12223717>
- [67] S.K. Kirthika, S.K. Singh, Durability studies on recycled fine aggregate concrete, *Construction and Building Materials* 250 (2020) 118850, <https://doi.org/10.1016/j.conbuildmat.2020.118850>
- [68] C.J. Engelsen, H.A. van der Sloot, G. Wibetoe, G. Petkovic, E. Stoltenberg-Hansson, W. Lund, Release of major elements from recycled concrete aggregates and geochemical modelling, *Cement and Concrete Research* 39 (2009) 446–459, <https://doi.org/10.1016/j.cemconres.2009.02.001>
- [69] M.E. Sosa, L.E. Carrizo, C.J. Zega, Y.A. Villagrán Zaccardi, Water absorption of fine recycled aggregates: effective determination by a method based on electrical conductivity, *Materials and Structures* (2018) 51:127, <https://doi.org/10.1617/s11527-018-1248-2>
- [70] C.J. Zega, Propiedades físico-mecánicas y durables de hormigones reciclados. Facultad De Ingeniería. Universidad Nacional de La Plata, 2010, p. 166.
- [71] M.E. Bouarroudj, S. Remond, F. Michel, Z. Zhao, D. Bulteel, L. Courard, Use of a reference limestone fine aggregate to study the fresh and hard behavior of mortar made with recycled fine aggregate, *Materials and Structures* (2019) 52:18, <https://doi.org/10.1617/s11527-019-1325-1>
- [72] Z. Li, J. Liu, P. Zhong, Assessment of the absorption of fine recycled aggregates in paste – determination of free water content of paste. In 4th International Conference On Service Life Design For Infrastructure, 2018, Delft.
- [73] H. Maimouni, S. Remond, F. Huchet, P. Richard, V. Thiery, Y. Descantes, Quantitative assessment of the saturation degree of model fine recycled concrete aggregates immersed in a filler or cement paste, *Construction and Building Materials* 175 (2018) 496–507, <https://doi.org/10.1016/j.conbuildmat.2018.04.211>
- [74] M. Velay-Lizancos, I. Martínez-Lage, C. Vázquez-Herrero, P. Vázquez-Burgo, Empirical definition of effective water/cement ratio in mortars with recycled aggregate depending on the absorption, *Proceedings of the II International and IV National Congress on Sustainable Construction and Eco-Efficient*

- Solutions Construction and Eco-efficient Solutions, Sevilla, 2015.
- [75] Y. Leng, Y. Rui, S. Zhonghe, F. Dingqiang, W. Jinnan, Y. Yonghuan, L. Qiqing, H. Xiang, Development of an environmental Ultra-High Performance Concrete (UHPC) incorporating carbonated recycled coarse aggregate, *Construction and Building Materials* 362 (2023) 129657, <https://doi.org/10.1016/j.conbuildmat.2022.129657>
- [76] C. Liang, N. Lua, H. Ma, Z. Ma, Z. Duan, Carbonation behavior of recycled concrete with CO₂-curing recycled aggregate under various environments, *Journal of CO₂ Utilization* 39 (2020) 101185, <https://doi.org/10.1016/j.jcou.2020.101185>
- [77] J. Zhang, C. Shi, Y. Li, X. Pan, C.S. Poon, Z. Xie, Influence of carbonated recycled concrete aggregate on properties of cement mortar, *Construction and Building Materials* 98 (2015) 1–7, <http://dx.doi.org/10.1016/j.conbuildmat.2015.08.087>
- [78] Y. Jiang, L. Li, J. Lu, P. Shen, T.-C. Ling, C.S. Poon, Enhancing the microstructure and surface texture of recycled concrete fine aggregate via magnesium-modified carbonation, *Cement and Concrete Research* 162 (2022) 106967, <https://doi.org/10.1016/j.cemconres.2022.106967>
- [79] M.T. Le, C. Tribout, G. Escadeillas, Durability of mortars with leftover recycled sand, *Construction and Building Materials* 215 (2019) 391–400, <https://doi.org/10.1016/j.conbuildmat.2019.04.179>
- [80] M. Sereng, A. Djerbi, O.O. Metalssi, P. Dangla, J.-M. Torrenti, Improvement of Recycled Aggregates Properties by Means of CO₂ Uptake, *Appl. Sci.* 2021, 11, 6571, <https://doi.org/10.3390/app11146571>
- [81] C. Shi, Z. Wu, Z. Cao, T.C. Ling, J. Zheng, Performance of mortar prepared with recycled concrete aggregate enhanced by CO₂ and pozzolan slurry, *Cement and Concrete Composites* 86 (2018) 130–138, <https://doi.org/10.1016/j.cemconcomp.2017.10.013>
- [82] G. Pan, M. Zhan, M. Fu, Y. Wanga, X. Lu, Effect of CO₂ curing on demolition recycled fine aggregates enhanced by calcium hydroxide pre-soaking, *Construction and Building Materials* 154 (2017) 810–818, <http://dx.doi.org/10.1016/j.conbuildmat.2017.07.079>
- [83] Y. Jiang, L. Li, J.-x. Lu, P. Shen, T.-C. Ling, C.S. Poon, Mechanism of carbonating recycled concrete fines in aqueous environment: the particle size effect, *Cem. Concr. Compos.* 133 (2022), 104655, <https://doi.org/10.1016/j.cemconcomp.2022.104655>
- [84] M. Zajac, J. Skibsted, J. Skocek, P. Durdzinski, F. Bullerjahn, M. Ben, Phase assemblage and microstructure of cement paste subjected to enforced, wet carbonation, *Cement Concr. Res.* 130, 105990, <https://doi.org/10.1016/j.cemconres.2020.105990>
- [85] M. Zajac, J. Skibsted, P. Durdzinski, F. Bullerjahn, J. Skocek, M. Ben Haha, Kinetics of enforced carbonation of cement paste. *Cement Concr. Res.* 131 (2020), 106013, <https://doi.org/10.1016/j.cemconres.2020.106013>
- [86] V.W.Y. Tam, X.F. Gao, C.M. Tam, Microstructural analysis of recycled aggregate concrete produced from two-stage mixing approach, *Cement and Concrete Research* 35 (2005) 1195–1203, <https://doi.org/10.1016/j.cemconres.2004.10.025>
- [87] J.-M. Torrenti et al., The FastCarb project: Taking advantage of the accelerated carbonation of recycled concrete aggregates, *Case Studies in Construction Materials* 17 (2022) e01349, <https://doi.org/10.1016/j.cscm.2022.e01349>
- [88] G. Chinzorig, M.K. Lim, M. Yu, H. Lee, O. Enkbold, D. Choi, Strength, shrinkage and creep and durability aspects of concrete including CO₂ treated recycled fine aggregate, *Cement and Concrete Research* 136 (2020) 106062, <https://doi.org/10.1016/j.cemconres.2020.106062>
- [89] J.-S. Ha, J.-H. Shin, L. Chung, H.-S. Kim, Performance Evaluation of Recycled Aggregate Concrete Made of Recycled Aggregate Modified by Carbonation, *Journal of the Korea Concrete Institute* Vol. 28, No. 4, pp. 445–454, 2016, <http://dx.doi.org/10.4334/JKCI.2016.28.4.445>
- [90] J. Tiefenthaler, L. Braune, C. Bauer, R. Sacchi, M. Mazzotti, Technological Demonstration and Life Cycle Assessment of a Negative Emission Value Chain in the Swiss Concrete Sector, *Frontiers in Climate* 3:729259 (2021), <http://doi.org/10.3389/fclim.2021.729259>
- [91] S. Li, J. Gao, Q. Li, X. Zhao, Investigation of using recycled powder from the preparation of recycled aggregate as a supplementary cementitious material, *Constr. Build. Mater.* 267 (2021), 120976, <https://doi.org/10.1016/j.conbuildmat.2020.120976>
- [92] H. Zhang, C. Zhang, B. He, S. Yi, L. Tang, Recycling fine powder collected from construction and demolition wastes as partial alternatives to cement: A comprehensive analysis on effects, mechanism, cost and CO₂ emission, *Journal of Building Engineering* 71 (2023) 106507, <https://doi.org/10.1016/j.jobe.2023.106507>
- [93] M. Zajac, J. Skocek, J. Skibsted, M. Ben Haha, CO₂ mineralization of demolished concrete wastes into a supplementary cementitious material – a new CCU approach for the cement industry, *RILEM Technical Letters* (2021) 6: 53–60, <https://doi.org/10.21809/rilemtechlett.2021.141>
- [94] M. Zajac, J. Skocek, Ł. Gołek, J. Deja, Supplementary cementitious materials based on recycled concrete paste, *J. Clean. Prod.* 387 (2023) 135743, <https://doi.org/10.1016/j.jclepro.2022.135743>
- [95] S.K. Kaliyavaradhan, L. Li, T.-C. Ling, Response surface methodology for the optimization of CO₂ uptake using waste concrete powder, *Construction and Building Materials* 340 (2022) 127758, <https://doi.org/10.1016/j.conbuildmat.2022.127758>
- [96] J. Skocek, M. Zajac, M. Ben Haha, Carbon Capture and Utilization by mineralization of cement pastes derived from recycled concrete, *Scientific Reports* (2020) 10:5614, <https://doi.org/10.1038/s41598-020-62503-z>
- [97] P. Shen, Y. Zhang, Y. Jiang, B. Zhan, J. Lu, S. Zhang, D. Xuan, C.S. Poon, Phase assemblage evolution during wet carbonation of recycled concrete fines, *Cem. Concr. Res.* 154 (2022), 106733, <https://doi.org/10.1016/j.cemconres.2022.106733>
- [98] B. Lu, C. Shi, J. Zhang, J. Wang, Effects of carbonated hardened cement paste powder on hydration and microstructure of Portland cement, *Construct. Build. Mater.* 186 (2018) 699–708, <https://doi.org/10.1016/j.conbuildmat.2018.07.159>
- [99] H. Mehdizadeh, T.C. Ling, X. Cheng, K.H. Mo, Effect of particle size and CO₂ treatment of waste cement powder on properties of cement paste, *Can. J. Civ.*

- Eng. 48 (2021) 522–531, <https://doi.org/10.1139/cjce-2019-0574>
- [100] L. Qin, X. Gao, Recycling of waste autoclaved aerated concrete powder in Portland cement by accelerated carbonation, *Waste Management* 89 (2019) 254–264, <https://doi.org/10.1016/j.wasman.2019.04.018>
- [101] H. Wu, C. Liang, J. Xiao, Z. Ma, Properties and CO₂-curing enhancement of cement-based materials containing various sources of waste hardened cement paste powder, *J. Build. Eng.* 44 (2021), 102677, <https://doi.org/10.1016/j.jobe.2021.102677>.
- [102] H. Mehdizadeh, X. Cheng, K.H. Mo, T.C. Ling, Upcycling of waste hydrated cement paste containing high-volume supplementary cementitious materials via CO₂ pre-treatment, *J. Build. Eng.* 52 (2022), 104396, <https://doi.org/10.1016/j.jobe.2022.104396>
- [103] A. Carriço, J.A. Bogas, S. Hu, S. Real, M.F.C. Pereira, Novel separation process for obtaining recycled cement and high-quality recycled sand from waste hardened concrete, *Journal of Cleaner Production* 309 (2021) 127375, <https://doi.org/10.1016/j.jclepro.2021.127375>
- [104] A. Akbarnezhad, K.C.G. Ong, M.H. Zhang, C.T. Tam, T.W.J. Foo, Microwave-assisted beneficiation of recycled concrete aggregates, *Construction and Building Materials* 25 (2011) 3469–3479, <https://doi.org/10.1016/j.conbuildmat.2011.03.038>
- [105] W. de Vries, ADR The use of Advanced Dry Recovery in recycling fine moist granular materials, TU Delft, 2017, 10.4233/uuid:c3c8578d-fd2c-493f-b4c5-79e63bc6d70c
- [106] S. Lotfi, J. Deja, P. Rem, R. Mróz, E. van Roekel, H. van der Stelt, Mechanical recycling of EOL concrete into high-grade aggregates, *Resources, Conservation and Recycling* 87 (2014) 117–125, <http://dx.doi.org/10.1016/j.resconrec.2014.03.010>
- [107] S. Lotfi, P. Rem, Recycling of End of Life Concrete Fines into Hardened Cement and Clean Sand, *Journal of Environmental Protection* (2016), 7, 934–950, <http://dx.doi.org/10.4236/jep.2016.76083>
- [108] J. Moreno-Juez, I.J. Vegas, A.T. Gebremariam, V. García-Cortés, F. Di Maio, Treatment of end-of-life concrete in an innovative heating-air classification system for circular cement-based products, *Journal of Cleaner Production* 263 (2020) 121515, <https://doi.org/10.1016/j.jclepro.2020.121515>
- [109] M.V.A. Florea, H.J.H. Brouwers, Properties of various size fractions of crushed concrete related to process conditions and re-use, *Cement and Concrete Research* 52 (2013) 11–21, <http://dx.doi.org/10.1016/j.cemconres.2013.05.005>
- [110] <http://www.c2ca.eu/activities/the-recyclingprocess/>
- [111] X. Fang, D. Xuan, C.S. Poon, Empirical modelling of CO₂ uptake by recycled concrete aggregates under accelerated carbonation conditions, *Materials and Structures* (2017) 50:200, <https://doi.org/10.1617/s11527-017-1066-y>
- [112] H.-J. Ho, A. Iizuka, E. Shibata, H. Tomita, K. Takano, T. Endo, Utilization of CO₂ in direct aqueous carbonation of concrete fines generated from aggregate recycling: Influences of the solid–liquid ratio and CO₂ concentration, *J. Clean Prod.* 312 (2021), 127832, <https://doi.org/10.1016/j.jclepro.2021.127832>
- [113] A.B. Ghacham, L.-C. Pasquier, E. Cecchi, J.-F. Blais, G. Mercier, Valorization of waste concrete through CO₂ mineral carbonation: Optimizing parameters and improving reactivity using concrete separation, *Journal of Cleaner Production* 166 (2017) 869–878, <http://dx.doi.org/10.1016/j.jclepro.2017.08.015>
- [114] L.-C. Pasquier, N. Kemache, J. Mocellin, J.-F. Blais, G. Mercier, Waste Concrete Valorization; Aggregates and Mineral Carbonation Feedstock Production, *Geosciences* 2018, 8, 342, <https://doi.org/10.3390/geosciences8090342>
- [115] Y. Zhang, H. Chen, Q. Wang, Accelerated carbonation of regenerated cementitious materials from waste concrete for CO₂ sequestration, *Journal of Building Engineering* 55 (2022) 104701, <https://doi.org/10.1016/j.jobe.2022.104701>
- [116] A. Dindi, D.V. Quang, L.F. Vega, E. Nashef, M.R.M. Abu-Zahra, Applications of fly ash for CO₂ capture, utilization, and storage, *Journal of CO₂ Utilization* 29 (2019) 82–102, <https://doi.org/10.1016/j.jcou.2018.11.011>
- [117] Mineral Commodity Summaries 2022 By: U.S. Geological Survey, <https://doi.org/10.3133/mcs2022>
- [118] S.-Y. Pan, R. Adhikari, Y.-H. Chen, P. Li, P.-C. Chiang, Integrated and innovative steel slag utilization for iron reclamation, green material production and CO₂ fixation via accelerated carbonation, *J. Clean. Prod.* 137 (2016) 617–631, <https://doi.org/10.1016/j.jclepro.2016.07.112>
- [119] Z. Chen, Z. Cang, F. Yang, J. Zhang, L. Zhang, Carbonation of steelmaking slag presents an opportunity for carbon neutral: A review, *Journal of CO₂ Utilization* 54 (2021) 101738, <https://doi.org/10.1016/j.jcou.2021.101738>
- [120] S. Wang, J. Kim, T. Qin, Mineral carbonation of iron and steel by-products: State-of-the-art techniques and economic, environmental, and health implications, *Journal of CO₂ Utilization* 81 (2024) 102707, <https://doi.org/10.1016/j.jcou.2024.102707>
- [121] G. Montes-Hernandez, R. Pérez-López, F. Renard, J.M. Nieto, L. Charlet, Mineral sequestration of CO₂ by aqueous carbonation of coal combustion fly-ash, *J. Hazard. Mater.* 161 (2009) 1347–1354, <https://doi.org/10.1016/j.jhazmat.2008.04.104>
- [122] H.Y. Jo, J.H. Kim, Y.J. Lee, M. Lee, S.J. Choh, Evaluation of factors affecting mineral carbonation of CO₂ using coal fly ash in aqueous solutions under ambient conditions, *Chem. Eng. J.* 183 (2012) 77–87, <https://doi.org/10.1016/j.cej.2011.12.023>
- [123] A. Ebrahimi, M. Saffari, D. Milani, A. Montoya, M. Valix, A. Abbas, Sustainable transformation of fly ash industrial waste into a construction cement blend via CO₂ carbonation, *J. Clean. Prod.* 156 (2017) 660–669, <https://doi.org/10.1016/j.jclepro.2017.04.037>
- [124] A. González, N. Moreno, R. Navia, CO₂ carbonation under aqueous conditions using petroleum coke combustion fly ash, *Chemosphere* 117 (2014) 139–143, <https://doi.org/10.1016/j.chemosphere.2014.06.034>
- [125] Y. Sun, V. Parikh, L. Zhang, Sequestration of carbon dioxide by indirect mineralization using Victorian brown coal fly ash, *J. Hazard. Mater.* 209–210 (2012) 458–466, <https://doi.org/10.1016/j.jhazmat.2012.01.053>
- [126] A. Mazzella, M. Errico, D. Spiga, CO₂ uptake capacity of coal fly ash: influence of pressure and temperature on direct gas-solid carbonation, *J. Environ. Chem. Eng.* 4 (2016) 4120–4128, <https://doi.org/10.1016/j.jece.2016.09.020>

- [127] A. Ćwik, I. Casanova, K. Rausis, K. Zarebska, Utilization of high-calcium fly ashes through mineral carbonation: the cases for Greece, Poland and Spain, *J. CO₂ Util.* 32 (2019) 155–162, <https://doi.org/10.1016/j.jcou.2019.03.020>
- [128] E. Ren, S. Tang, C. Liu, H. Yue, C. Li, B. Liang, Carbon dioxide mineralization for the disposition of blast-furnace slag: reaction intensification using NaCl solutions, *Greenh. Gases: Sci. Technol.* 10 (2020) 436–448. [10.1002/ghg.1837](https://doi.org/10.1002/ghg.1837)
- [129] S. Lee, J.-W. Kim, S. Chae, J.-H. Bang, S.-W. Lee, CO₂ sequestration technology through mineral carbonation: an extraction and carbonation of blast slag, *J. CO₂ Util.* 16 (2016) 336–345, <https://doi.org/10.1016/j.jcou.2016.09.003>
- [130] M. Mun, H. Cho, Mineral carbonation for carbon sequestration with industrial waste, *Energy Procedia* 37 (2013) 6999–7005, <https://doi.org/10.1016/j.egypro.2013.06.633>
- [131] E.E. Chang, C.-H. Chen, Y.-H. Chen, S.-Y. Pan, P.-C. Chiang, Performance evaluation for carbonation of steel-making slags in a slurry reactor, *J. Hazard. Mater.* 186 (1) (2011) 558–564, <https://doi.org/10.1016/j.jhazmat.2010.11.038>
- [132] E.E. Chang, A.-C. Chiu, S.-Y. Pan, Y.-H. Chen, C.-S. Tan, P.-C. Chiang, Carbonation of basic oxygen furnace slag with metalworking wastewater in a slurry reactor, *Int. J. Greenh. Gas Control.* 12 (2013) 382–389, <https://doi.org/10.1016/j.ijggc.2012.11.026>
- [133] E.E. Chang, T.-L. Chen, S.-Y. Pan, Y.-H. Chen, P.-C. Chiang, Kinetic modeling on CO₂ capture using basic oxygen furnace slag coupled with cold-rolling wastewater in a rotating packed bed, *J. Hazard. Mater.* 260 (2013) 937–946, <https://doi.org/10.1016/j.jhazmat.2013.06.052>
- [134] A. Poletini, R. Pomi, A. Stramazzo, Carbon sequestration through accelerated carbonation of BOF slag: influence of particle size characteristics, *Chem. Eng. J.* 298 (2016) 26–35, <https://doi.org/10.1016/j.cej.2016.04.015>
- [135] R. Baciocchi, G. Costa, M. Di Gianfilippo, A. Poletini, R. Pomi, A. Stramazzo, Thin-film versus slurry-phase carbonation of steel slag: CO₂ uptake and effects on mineralogy, *J. Hazard. Mater.* 283 (2015) 302–313, <https://doi.org/10.1016/j.jhazmat.2014.09.016>
- [136] A.B. Ghacham, L.-C. Pasquier, E. Cecchi, J.-F. Blais, G. Mercier, CO₂ sequestration by mineral carbonation of steel slags under ambient temperature: parameters influence, and optimization, *Environ. Sci. Pollut. Res. - Int.* 23 (17) (2016) 17635–17646, <https://doi.org/10.1007/s11356-016-6926-4>
- [137] T.D. Rushendra Revathy, K. Palanivelu, A. Ramachandran, Direct mineral carbonation of steelmaking slag for CO₂ sequestration at room temperature, *Environ. Sci. Pollut. Res. - Int.* 23 (8) (2016) 7349–7359, <https://doi.org/10.1007/s11356-015-5893-5>
- [138] D. Xuan, B. Zhan, C.S. Poon, W. Zheng, Carbon dioxide sequestration of concrete slurry waste and its valorisation in construction products, *Constr. Build. Mater.* 113 (2016) 664–672, <https://doi.org/10.1016/j.conbuildmat.2016.03.109>
- [139] P. Tang, D. Xuan, H.W. Cheng, C.S. Poon, D.C.W. Tsang, Use of CO₂ curing to enhance the properties of cold bonded lightweight aggregates (CBLAs) produced with concrete slurry waste (CSW) and fine incineration bottom ash (IBA), *J. Hazard. Mater.* 381 (2020), 120951, <https://doi.org/10.1016/j.jhazmat.2019.120951>
- [140] S.K. Kaliyavaradhan, T.C. Ling, K.H. Mo, CO₂ sequestration of fresh concrete slurry waste: optimization of CO₂ uptake and feasible use as a potential cement binder, *J. CO₂ Util.* 42 (2020), 101330, <https://doi.org/10.1016/j.jcou.2020.101330>
- [141] D. Medas, G. Cappai, G. De Giudici, M. Piredda, S. Podda, Accelerated carbonation by cement kiln dust in aqueous slurries: chemical and mineralogical investigation, *Greenh. Gases Sci. Technol.* 7 (2017) 692–705, <https://doi.org/10.1002/ghg.1681>
- [142] D.N. Huntzinger, J.S. Gierke, S.K. Kawatra, T.C. Eisele, L.L. Sutter, Carbon dioxide sequestration in cement kiln dust through mineral carbonation, *Environ. Sci. Technol.* 43 (2009) 1986–1992, <https://doi.org/10.1021/es802910z>
- [143] D. Sharma, S. Goyal, Accelerated carbonation curing of cement mortars containing cement kiln dust: an effective way of CO₂ sequestration and carbon footprint reduction, *J. Clean. Prod.* 192 (2018) 844–854, <https://doi.org/10.1016/j.jclepro.2018.05.027>
- [144] D.N. Huntzinger, J.S. Gierke, L.L. Sutter, S.K. Kawatra, T.C. Eisele, Mineral carbonation for carbon sequestration in cement kiln dust from waste piles, *J. Hazard. Mater.* 168 (2009) 31–37, <https://doi.org/10.1016/j.jhazmat.2009.01.122>
- [145] R.M. Santos, J. Van Bouwel, E. Vandevelde, G. Mertens, J. Elsen, T. Van Gerven, Accelerated mineral carbonation of stainless steel slags for CO₂ storage and waste valorization: effect of process parameters on geochemical properties, *Int. J. Greenh. Gas Control* 17 (2013) 32–45, <https://doi.org/10.1016/j.ijggc.2013.04.004>
- [146] Q. Song, M.Z. Guo, L. Wang, T.C. Ling, Use of steel slag as sustainable construction materials: a review of accelerated carbonation treatment, *Resour. Conserv. Recycl.* 173 (2021), 105740, <https://doi.org/10.1016/j.resourcon.2021.105740>
- [147] M.S. Ko, Y.L. Chen, J.H. Jiang, Accelerated carbonation of basic oxygen furnace slag and the effects on its mechanical properties, *Constr. Build. Mater.* 98 (2015) 286–293, <https://doi.org/10.1016/j.conbuildmat.2015.08.051>
- [148] B. Pang, Z. Zhou, H. Xu, Utilization of carbonated and granulated steel slag aggregate in concrete, *Constr. Build. Mater.* 84 (2015) 454–467, <https://doi.org/10.1016/j.conbuildmat.2015.03.008>
- [149] B. Pang, Z. Zhou, X. Cheng, P. Du, H. Xu, ITZ properties of concrete with carbonated steel slag aggregate in salty freeze-thaw environment, *Constr. Build. Mater.* 114 (2016) 162–171, <https://doi.org/10.1016/j.conbuildmat.2016.03.168>
- [150] M. Bodor, R.M. Santos, G. Cristea, M. Salman, Ó. Cizer, R.I. Iacobescu, Y. W. Chiang, K. Van Balen, M. Vlad, T. Van Gerven, Laboratory investigation of carbonated BOF slag used as partial replacement of natural aggregate in cement mortars, *Cem. Concr. Compos.* 65 (2016) 55–66, <https://doi.org/10.1016/j.cemconcomp.2015.10.002>
- [151] Y. Jiang, T. Ling, Production of artificial aggregates from steel-making slag: influences of accelerated carbonation during granulation and/or post-curing, *J. CO₂ Util.* 36, (2020) 135–144, <https://doi.org/10.1016/j.jcou.2019.11.009>

- [152] L. Mo, S. Yang, B. Huang, L. Xu, S. Feng, M. Deng, Preparation, microstructure and property of carbonated artificial steel slag aggregate used in concrete, *Cement and Concrete Composites* 113 (2020) 103715, <https://doi.org/10.1016/j.cemconcomp.2020.103715>
- [153] W. Shen, Y. Liu, M. Wu, D. Zhang, X. Du, D. Zhao, G. Xu, B. Zhang, X. Xiong, Ecological carbonated steel slag pervious concrete prepared as a key material of sponge city, *Journal of Cleaner Production* 256 (2020) 120244, <https://doi.org/10.1016/j.jclepro.2020.120244>
- [154] L. Li, Y. Jiang, S.-Y. Pan, T.-C. Ling, Comparative life cycle assessment to maximize CO₂ sequestration of steel slag products, *Construction and Building Materials* 298 (2021) 123876, <https://doi.org/10.1016/j.conbuildmat.2021.123876>
- [155] S.L. Pei, S.Y. Pan, X. Gao, Y.K. Fang, P.C. Chiang, Efficacy of carbonated petroleum coke fly ash as supplementary cementitious materials in cement mortars, *J. Clean. Prod.* 180 (2018) 689–697, <https://doi.org/10.1016/j.jclepro.2018.01.055>
- [156] S. Sahoo, B.B. Das, S. Mustakim, Acid, alkali, and chloride resistance of concrete composed of low-carbonated fly ash, *J. Mater. Civ. Eng.* 29 (2017), 04016242, [https://doi.org/10.1061/\(asce\)mt.1943-5533.0001759](https://doi.org/10.1061/(asce)mt.1943-5533.0001759)
- [157] Z. Chen, R. Li, J. Liu, Preparation and properties of carbonated steel slag used in cement cementitious materials, *Constr. Build. Mater.* 283 (2021), 122667, <https://doi.org/10.1016/j.conbuildmat.2021.122667>
- [158] S.Y. Pan, T.C. Chung, C.C. Ho, C.J. Hou, Y.H. Chen, P.C. Chiang, CO₂ mineralization and utilization using steel slag for establishing a waste-to-resource supply chain, *Sci. Rep.* 7 (2017) 1–11, <https://doi.org/10.1038/s41598-017-17648-9>
- [159] X. Wang, W. Ni, J. Li, S. Zhang, M. Hitch, R. Pascual, Carbonation of steel slag and gypsum for building materials and associated reaction mechanisms, *Cem. Concr. Res.* 125 (2019), 105893, <https://doi.org/10.1016/j.cemconres.2019.105893>
- [160] Kunal, R. Siddique, A. Rajor, Use of cement kiln dust in cement concrete and its leachate characteristics, *Resour. Conserv. Recycl.* 61 (2012) 59–68, <https://doi.org/10.1016/j.resconrec.2012.01.006>